Ministry of
Northern Development
and Mines
Ontario

Aggregate Resources Inventory of
St. Vincent Township
Grey County

Ontario Geological Survey
Aggregate Resources Inventory
Paper 131

By Staff of the Engineering and Terrain Geology Section,
Ontario Geological Survey

1992

© Queen's Printer for Ontario, 1992

ISSN 0708–2061
ISBN 0-7743-9934-1

Publications of the Ontario Geological Survey and the Ministry of Northern Development and Mines are available from the following sources. Orders for publications should be accompanied by cheque or money order payable to the *Treasurer of Ontario*.

Reports, maps and price lists (personal shopping or mail order):

Natural Resources Information Centre
Room M1-73, Macdonald Block
900 Bay Street
Toronto, Ontario M7A 2C1
(416) 314–2000 Collect calls accepted

Reports and accompanying maps only (personal shopping):

Publications Ontario
Main Floor, 880 Bay Street
Toronto, Ontario M7A 1N8

Canadian Cataloguing in Publication Data

Main entry under title:

Aggregate resources inventory of St. Vincent Township, Grey County

(Ontario Geological Survey aggregate resources
inventory paper, ISSN 0708–2061 ; 131)
ISBN 0–7743–9934–1

1. Aggregates (Building materials)—Ontario—St. Vincent
I. Ontario Geological Survey. Engineering and Terrain Geology Section.
II. Ontario. Mines and Minerals Division. III. Ontario Geological Survey.
IV. Series.

TN939.A33 1991 553.6'2'0971318 C91–092552–6

Every possible effort is made to ensure the accuracy of the information contained in this report, but the Ministry of Northern Development and Mines does not assume any liability for errors that may occur. Source references are included in the report and users may wish to verify critical information.

If you wish to reproduce any of the text, tables or illustrations in this report, please write for permission to the Director, Ontario Geological Survey, Ministry of Northern Development and Mines, 11th Floor, 77 Grenville Street, Toronto, Ontario M7A 1W4.

Cette publication est disponsible en anglais seulement.

Parts of this publication may be quoted if credit is given. It is recommended that reference be made in the following form:

Ontario Geological Survey 1992. Aggregate resources inventory of St. Vincent Township; Ontario Geological Survey, Aggregate Resources Inventory Paper 131, 37p.

500–92–Maracle Press

92-05832/

Contents

Abstract v

Résumé vi

Introduction 3

Part I — Inventory Methods 4
- Field and Office Methods 4
- Resource Tonnage Calculation Techniques 4
  - Sand and Gravel Resources 4
  - Bedrock Resources 5
  - Units and Definitions 5

Part II — Data Presentation and Interpretation 6
- Map 1: Distribution of Sand and Gravel Deposits 6
  - Deposit Symbol 6
  - Texture Symbol 6
- Map 2: Selected Sand and Gravel Resource Areas 6
  - Site Specific Criteria 7
    - Deposit Size 7
    - Aggregate Quality 7
    - Location and Setting 8
  - Regional Considerations 8
- Map 3: Bedrock Resources 8
  - Selection Criteria 9
  - Selected Resource Areas 9

Part III—Assessment of Aggregate Resources in St. Vincent Township 10
- Location and Population 10
- Physiography and Surficial Geology 10
- Extractive Activity 11
- Selected Sand and Gravel Resource Areas 11
  - Selected Sand and Gravel Resource Area 1 11
- Bedrock Geology 12
  - Selected Bedrock Resource Areas 1 and 2 13
- Summary 13

References 22

Appendix A — Suggested Additional Reading 23

Appendix B — Glossary 24

Appendix C — Geology of Sand and Gravel Deposits 26

Appendix D — Geology of Bedrock Deposits 28

Appendix E — Aggregate Quality Test Specifications 35

Conversion Factors for Measurements in Ontario Geological Survey Publications 37

TABLES

1. Total Sand and Gravel Resources, St. Vincent Township 14
2. Sand and Gravel Pits, St. Vincent Township 15
3. Selected Sand and Gravel Resource Areas, St. Vincent Township 16
4. Total Identified Bedrock Resources, St. Vincent Township 17
5. Quarries, St. Vincent Township 18

6. Selected Bedrock Resource Areas, St. Vincent Township 18
7. Summary of Test Hole Data, St. Vincent Township 19
8. Summary of Geophysics Data, St. Vincent Township 19
9. Results of Aggregate Quality Tests, St. Vincent Township 19

FIGURES

1. Key Map Showing the Location of St. Vincent Township, Scale 1:1 800 000 v
2a–2b. Aggregate Grading Curves, St. Vincent Township 20

GEOLOGICAL MAPS (back pocket)

1. Distribution of Sand and Gravel Deposits, St. Vincent Township, Scale 1:50 000.
2. Selected Sand and Gravel Resource Areas, St. Vincent Township, Scale 1:50 000.
3. Bedrock Resources, St. Vincent Township, Scale 1:50 000.

Abstract

This report includes an inventory and evaluation of sand, gravel and bedrock resources in St. Vincent Township. The report is part of the Aggregate Assessment Office's inventory of aggregate resources in areas designated under the Aggregate Resources Act.

Surficial deposits in St. Vincent Township include ice-contact stratified drift, glaciolacustrine and beach deposits. Five glaciolacustrine beach deposits have been selected for possible resource protection at the primary level of significance. These deposits have a combined unlicenced area of 1250 acres (510 ha). An estimated 890 acres (360 ha) are currently available for extraction and contain possible resources of 18 million tons (16 million tonnes). Future extraction of aggregate from these glaciolacustrine beaches may be inhibited because: 1) parts of these beaches are in a specialty crop area, 2) there has been extensive previous extraction and 3) there are residential, commercial and industrial developments.

There are several bedrock formations of Late Ordovician and Early and Middle Silurian ages which underlie the township. Possible aggregate resources derived from bedrock are available from the Amabel and Manitoulin formations. The Amabel Formation is a valuable potential source of crushed stone, concrete aggregate, building stone and lime. Dolostone from the Manitoulin Formation has been extracted from a quarry site to supplement the township's requirements for base and subbase road-building materials. In areas where the drift cover is less than 25 feet (8 m), the Amabel Formation has been selected for possible resource protection. The Manitoulin Formation dolostone has not been selected because of the presence of the higher quality Amabel Formation within the township. The Selected Bedrock Resource Areas contain possible resources of approximately 560 million tons (510 million tonnes).

Selected Resource Areas are not intended to be permanent, single land use units. They represent areas in which a major resource is known to exist and may be reserved wholly or partially for extractive development and/or resource protection.



Figure 1. Key map showing the location of St. Vincent Township, scale 1:1 800 000.

Résumé

Ce rapport comprend à la fois un inventaire et une évaluation des ressources en sable et en gravier ainsi que des ressources du substratum dans le canton de St Vincent. Ce rapport fait partie de l'inventaire en cours par le Bureau d'évaluation des agrégats sur les ressources en agrégat dans les secteurs régis par la Loi sur les ressources en agrégat.

Les dépôts superficiels dans le canton de St Vincent comprennent du drift de contact glaciaire stratifié, des dépôts de plage et des dépôts glaciolacustres. Cinq dépôts de plage glaciolacustre ont été sélectionnés comme éventuelles réserves de ressources de première importance. Ces dépôts représentent une surface combinée, non enregistrée, de 1250 acres (510 ha). Environ 890 acres (360 ha) sont actuellement disponibles pour extraction et contiennent des ressources estimées à 18 millions de tonnes courtes (16 millions de tonnes métriques). L'extraction d'agrégat à partir de ces plages glaciolacustres risque d'être interdite dans l'avenir parce que : 1) ces plage se trouvent en partie dans un secteur de culture spécialisée, 2) ce secteur a déjà fait l'objet d'extraction extensive et 3) des zones résidentielles spécialisée, commerciales et industrielles se trouvent à proximité.

On trouve plusieurs formations rocheuses de l'Ordovicien supérieur et du Silurien inférieur à moyen dans le canton. Des ressources en agrégat dérivées du socle rocheux sont éventuellement disponibles à partir des formations d'Amabel et de Manitoulin. La Formation d'Amabel représente une excellente source potentielle de pierre concassée, de granulat pour le béton, de pierre de construction et de chaux. La dolomie qui constitue la Formation de Manitoulin a été extraite à partir d'une carrière pour subvenir aux besoins du canton en matière de matériaux de construction pour la couche de base et la couche de fondation des routes. Là où l'épaisseur de la couverture de drift est inférieure à 25 pieds (8 m), la Formation d'Amabel a été choisie comme réserve éventuelle. La dolomie de la Formation de Manitoulin n'a pas été sélectionnée du fait de la présence dans le canton de la Formation d'Amabel qui est de qualité supérieure. La zone sélectionnée pour les ressources de son substratum contient environ 560 millions de tonnes courtes (510 millions de tonnes métriques) de ressources.

Les zones sélectionnées pour leurs ressources ne sont pas destinées à un seul usage permanent. Elles représentent des zones dans lesquelles une ressource importante a été reconnue et peuvent être réservées entièrement ou partiellement pour l'exploitation et/ou comme réserves de ressources.

Cette publication est disponible en anglais seulement.

Aggregate Resources Inventory of
St. Vincent Township
Grey County

By Staff[1] of the Engineering and Terrain Geology Section

1. Project Supervisor: I. Szoke; field work and report by R. Gorman; compilation and drafting by Staff of the Engineering and Terrain Geology Section. Assistance with review provided by the Resident Geologist, Ministry of Northern Development and Mines, London, Ontario. The Mineral Resources Staff, Owen Sound District, Ministry of Natural Resources assisted in the collection of data, field checking and review of this report.

Manuscript accepted for publication by Chief, Engineering and Terrain Geology Section, January 18, 1992. This report is published by permission of V.G. Milne, Director, Ontario Geological Survey.

Introduction

Mineral aggregates, which include bedrock-derived crushed stone as well as naturally formed sand and gravel, constitute the major raw material in Ontario's road-building and construction industries. Very large amounts of these materials are used each year throughout the Province. For example, in 1987, the total tonnage of mineral aggregates extracted was 156 million tons (142 million tonnes), greater than that of any other metallic or nonmetallic commodity mined in the Province (Ontario Ministry of Northern Development and Mines 1989).

Although mineral aggregate deposits are plentiful in Ontario, they are fixed-location, nonrenewable resources which can be exploited only in those areas where they occur. Mineral aggregates are characterized by their high bulk and low unit value so that the economic value of a deposit is a function of its proximity to a market area as well as its quality and size. The potential for extractive development is usually greatest in urban fringe areas where land use competition is extreme. For these reasons the availability of adequate resources for future development is now being threatened in some areas.

Comprehensive planning and resource management strategies are required to make the best use of available resources, especially in those areas experiencing rapid development. Such strategies must be based on a sound knowledge of the total mineral aggregate resource base at both local and regional levels. The purpose of the Aggregate Resources Inventory is to provide the basic geological information required to include potential mineral aggregate resource areas in planning strategies and official plans. The reports should form the basis for discussion on those areas best suited for possible extraction. The aim is to assist decision-makers in protecting the public well-being by ensuring that adequate resources of mineral aggregate remain available for future use.

This report is a technical background document, based for the most part on geological information and interpretation. It has been designed as a component of the total planning process and should be used in conjunction with other planning considerations, to ensure the best use of a municipality's resources.

The report includes an assessment of sand and gravel resources as well as a discussion on the potential of bedrock-derived aggregate. The most recent information available has been used to prepare the report. As new information becomes available, revisions may be necessary.

Part I — Inventory Methods

FIELD AND OFFICE METHODS

The methods used to prepare the report primarily involve the interpretation of published geological data such as bedrock and surficial geology maps and reports (*see* References) as well as field examination of potential resource areas. Field methods include the examination of natural and man-made exposures of granular material. Most observations are made at quarries and sand and gravel pits located from records held by the Ontario Ministry of Transportation, the Ontario Geological Survey, and by Regional and District Offices of the Ontario Ministry of Natural Resources. Observations made at pit sites include estimates of the total face height and the proportion of gravel- and sand-sized fragments in the deposit. Observations are also made of the shape and lithology of the particles. These characteristics are important in estimating the quality and quantity of the aggregate. In areas of limited exposure, subsurface materials may be assessed by hand augering and test pitting, supplemented by test hole drilling, and geophysical surveys using hammer seismic equipment. The symbols for and locations of sample sites, test hole sites, and geophysical traverse lines are noted on Map 1.

Deposits with potential for further extractive development or those where existing data are scarce, are studied in greater detail. Representative layers in these deposits are sampled in 25- to 100-pound (11 to 45 kg) units from existing pit faces or from test pits. The samples are analyzed for grain size distribution, and in some cases absorption, Los Angeles abrasion, and Magnesium Sulphate soundness tests and petrographic analyses are carried out. Analyses are performed either in the laboratories of the Ontario Ministry of Transportation, or in the Geoscience Laboratory, Ontario Geological Survey.

The field data are supplemented by pit information on file with the Soils and Aggregates Section of the Ontario Ministry of Transportation. Data contained in these files include field estimates of the depth, composition and "workability" of deposits, as well as laboratory analyses of the physical properties and chemical suitability of the aggregate. Information concerning the development history of the pits and acceptable uses of the aggregate is also recorded. The location, size and depth of extraction of pits licenced under the Aggregate Resources Act are obtained from records held by Regional and District Offices of the Ontario Ministry of Natural Resources. The co-operation of the above-named groups in the compilation of inventory data is gratefully acknowledged.

Aerial photographs at various scales are used to determine the continuity of deposits, especially in areas where information is limited. Water well records, held by the Ontario Ministry of the Environment, are used in some areas to corroborate deposit thickness estimates or to indicate the presence of buried granular material. These records are used in conjunction with other evidence.

Topographic maps of the National Topographic System, at a scale of 1:50 000, are used as a compilation base for the field and office data. The information is then transferred to a base map, also at a scale of 1:50 000. These base maps are prepared by the Land and Resource Information Branch, Ontario Ministry of Natural Resources with information taken from maps of the National Topographic System by permission of Energy, Mines and Resources Canada, for presentation in the report.

RESOURCE TONNAGE CALCULATION TECHNIQUES

SAND AND GRAVEL RESOURCES

Once the interpretative boundaries of the aggregate units have been established, quantitative estimates of the possible resources available can be made. Generally, the volume of a deposit can be calculated if its areal extent and average thickness are known or can be estimated. The computation methods used are as follows. First, the area of the deposit, as outlined on the final base map, is calculated in acres. The thickness values used are an approximation of the deposit thickness, based on the face heights of pits developed in the deposit or on subsurface data such as test holes and water well logs. Original tonnage values can then be calculated by multiplying the volume of the deposit by 2500 (the density factor). This factor is approximately the number of tons in a one-foot (0.3 m) thick layer of sand and gravel, one acre (0.4 ha) in extent, assuming an average density of 110 pounds per cubic foot (1766 kg/m^3).

Tonnage = Area x Thickness x Density Factor

Tonnage calculated in this manner must be considered only as an estimate. Furthermore, such tonnages represent amounts that existed prior to any extraction of material (i.e., original tonnage) (Table 1, Column 4).

The Selected Sand and Gravel Resource Areas in Table 3 are calculated in the following way. Two successive subtractions are made from the total area. Column 3 accounts for the number of acres unavailable because of the presence of permanent cultural features and their associated setback requirements. Column 4 accounts for those areas that have previously been extracted (e.g., wayside and abandoned pits are included in this category). The remaining figure is the area of the deposit currently available for extraction (Column 5). The available area is then multiplied by the estimated deposit thickness and the density factor (Column 5 x Column 6 x 2500) to give an estimate of the sand and gravel

tonnage (Column 7) presently available for extractive development and/or resource protection.

Reserve estimates are calculated for deposits of primary significance. Reserve estimates for deposits of secondary and tertiary significance are not calculated in Table 3, however, the aggregate potential of these deposits is discussed in the report.

BEDROCK RESOURCES

The method used to calculate resources of bedrock-derived aggregate is much the same as that described above. The areal extent of bedrock formations overlain by less than 50 feet (15 m) of unconsolidated overburden is determined from bedrock geology maps, drift thickness and bedrock topography maps, and from the interpretation of water well records. The measured extent of such ar[illegible] is then multiplied by the estimated quarriable thick[illegible]s of the formation, based on stratigraphic analyses and on estimates of existing quarry faces in the unit. In some cases a standardized estimate of 60 feet (18 m) is used for thickness. Volume estimates are then multiplied by the density factor [the estimated weight in tons of a one-foot (0.3 m) thick section of rock, one acre (0.4 ha) in extent].

Resources of dolostone are calculated using a density factor of 165 pounds per cubic foot (2649 kg/m^3) or 3600 tons per acre (8070 t/ha). Sandstone resources are calculated using a density estimate of 146 pounds per cubic foot (2344 kg/m^3) and shale resources are calculated with a factor of 150 pounds per cubic foot (2408 kg/m^3).

UNITS AND DEFINITIONS

Although most of the measurements and other primary data available for resource tonnage calculations are given in Imperial units, Metric units have also been given in the text and on the tables which accompany the report. The Metric equivalent of the data is shown in brackets after or directly below the corresponding Imperial figures. Data are generally rounded off in accordance with the Ontario Metric Practice Guide (Metric Committee 1975).

The tonnage estimates made for sand and gravel deposits are termed possible resources (*see* Glossary, Appendix B) in accordance with terminology of the Ontario Resource Classification Scheme (Robertson 1975, p.7) and with the Association of Professional Engineers of Ontario (1976).

Part II — Data Presentation and Interpretation

Three maps, each portraying a different aspect of the aggregate resources in the municipality, accompany the report. Map 1, "Distribution of Sand and Gravel Deposits", gives a comprehensive inventory of the sand and gravel resources in the report area. Map 2, "Selected Sand and Gravel Resource Areas", shows those deposits which are considered to represent the largest and/or highest quality resources in the area. Map 3, "Bedrock Resources" shows the distribution of bedrock formations, the thickness of overlying unconsolidated sediments, and identifies the Selected Bedrock Resource Areas.

MAP 1: DISTRIBUTION OF SAND AND GRAVEL DEPOSITS

Map 1 is derived from existing surficial geology maps of the area or from aerial photograph interpretation in areas where surficial mapping is incomplete. The map shows the extent and quality of sand and gravel deposits within the study area and the present level of extractive activity.

On the map, gravel deposits are indicated by dark brown shading while sand deposits are shaded light brown. The present level of extractive activity is also indicated. Those areas which are licenced for extraction under the Aggregate Resources Act are shown by a solid outline and identified by a number which refers to the pit descriptions in Table 2. Each description notes the owner/operator, location and licenced acreage of the pit, as well as the estimated face height and percentage gravel. A number of unlicenced pits (abandoned pits or wayside pits operating on demand under authority of a permit) are identified by a numbered dot on Map 1 and described in Table 2. Similarly, test hole locations appear on Map 1 as a point symbol and are described in Table 7. Geophysics lines are shown on Map 1 by a line symbol and are interpreted in Table 8.

Map 1 also presents a summary of available information related to the quality of aggregate contained in all the known aggregate deposits in the study area. Much of this information is contained in the symbols which are found on the map. The Deposit Symbol appears for each mapped deposit and summarizes important genetic and textural data. The Texture Symbol is a circular proportional diagram which displays the grain size distribution of the aggregate in areas where bulk samples were taken.

DEPOSIT SYMBOL

The Deposit Symbol is similar to those used in soil mapping and land classification systems commonly in use in North America. The components of the symbol indicate the gravel content, thickness of material, origin (type) and quality limitations for every deposit shown on Map 1. These components are illustrated by the following example:



This symbol identifies an outwash deposit 10 to 20 feet (3 to 6 m) thick containing more than 35% gravel. Excess silt and clay may limit uses of the aggregate in the deposit.

The "gravel content" and "thickness class" are basic criteria for distinguishing different deposits. The "gravel content" symbol is an upper case "S" or "G". The "S" indicates that the deposit is generally "sandy" and that gravel-sized aggregate (greater than 4.75 mm) makes up less than 35% of the whole deposit. "G" indicates that the deposit contains more than 35% gravel.

The "thickness class" indicates a depth range which is related to the potential resource tonnage for each deposit. Four thickness class divisions have been established as shown in the legend for Map 1.

Two smaller sets of letters, divided from each other by a horizontal line, follow the thickness class number. The upper series of letters identifies the geologic deposit type (the deposit types are summarized with respect to their main geologic and extractive characteristics in Appendix C) and the lower series of letters identifies the main quality limitations that may be present in the deposit as discussed in the next section.

TEXTURE SYMBOL

The Texture Symbol provides a more detailed assessment of the grain size distribution of material sampled during field study. These symbols are derived from the information plotted on the aggregate grading curves found in the report. The relative amounts of gravel, sand, and silt and clay in the sampled material are shown graphically in the Texture Symbol by the subdivision of a circle into proportional segments. The following example shows a hypothetical sample consisting of 30% gravel, 60% sand and 10% silt and clay:

MAP 2: SELECTED SAND AND GRAVEL RESOURCE AREAS

Map 2 is an interpretative map derived from an evaluation of the deposits shown on Map 1. The deposits identified on Map 2 are those which are considered to be

important in ensuring an adequate resource base for the future.

All the selected sand and gravel resource areas are first delineated by geological boundaries and then classified into three levels of significance: primary, secondary and tertiary. Each area of primary significance is given a deposit number and all such deposits are shown by dark red shading on Map 2.

Selected Sand and Gravel Resource Areas of primary significance are not intended to be permanent, single land use units. They represent areas in which a major resource is known to exist and may be reserved wholly or partially for extractive development and/or resource protection.

Deposits of secondary significance are indicated by light red shading on Map 2. Such deposits are believed to contain significant amounts of sand and gravel. Although deposits of secondary significance are not considered to be the "best" resources in the report area, they may contain large quantities of sand and gravel and should be considered as part of the aggregate supply of the area.

Areas of tertiary significance are outlined on the map by a solid line but have no shading. They are not considered to be important resource areas because of their low available resources, or because of possible difficulties in extraction. Such areas may be useful for local needs but are unlikely to support large-scale development.

The process by which deposits are evaluated and selected involves the consideration of two sets of criteria. The main selection criteria are site specific, related to the characteristics of individual deposits. Factors such as deposit size, aggregate quality, and deposit location and setting are considered in the selection of those deposits best suited for extractive development. A second set of criteria involves the assessment of local aggregate resources in relation to the quality, quantity, and distribution of resources in the region in which the report area is located. The intent of such a process of evaluation is to ensure the continuing availability of sufficient resources to meet possible future demands.

SITE SPECIFIC CRITERIA

Deposit Size

Ideally, selected deposits should contain available sand and gravel resources large enough to support a commercial pit operation using a stationary or portable processing plant. In practice, much smaller deposits may be of significant value depending on the overall reserves in the rest of the municipality. Generally, deposits in Class 1 [greater than 20 feet (6 m) thick] and containing more than 35% gravel are considered to be most favourable for commercial development. Thinner deposits may be valuable in municipalities with low total resources.

Aggregate Quality

The limitations of natural aggregates for various uses result from variations in the lithology of the particles composing the deposit, and from variations in the size distribution of these particles.

Four indicators of the quality of aggregate may be included in the deposit symbols on Map 1. They are: gravel content (G or S), fines (C), oversize (O) and lithology (L).

Three of the quality indicators deal with grain size distribution. The gravel content (G or S) indicates the suitability of aggregate for various uses. Deposits containing at least 35% gravel in addition to a minimum of 20% material greater than the 26.5 mm sieve are considered to be the most favourable extractive sites, since this content is the minimum from which crushed products can be economically produced.

Excess fines (high silt and clay content) may severely limit the potential use of a deposit. Fines content in excess of 10% may impede drainage in road subbase aggregate and render it more susceptible to the effects of frost action. In asphalt aggregate, excess fines hinder the bonding of particles. Deposits known to have a high fines content are indicated by a "C" in the quality portion of the Deposit Symbol.

Deposits containing more than 20% oversize material [greater than 4 inches (10 cm) in diameter] may also have use limitations. The oversize component is unacceptable for all concrete aggregate and for road-building aggregate, so it must be either crushed or removed during processing. Deposits known to have an appreciable oversize component are indicated by an "O" in the quality portion of the Deposit Symbol.

Another indicator of the quality of an aggregate is lithology. Just as the unique physical and chemical properties of bedrock types determine their value for use as crushed rock, so do various lithologies of particles in a sand and gravel deposit determine its suitability for various uses. The presence of objectionable lithologies such as chert, siltstone and shale, even in relatively small amounts, can result in a reduction in the quality of an aggregate, especially for high quality uses such as concrete and asphalt. Similarly, highly weathered, very porous and friable rock can restrict the quality of an aggregate. Deposits known to contain objectionable lithologies are indicated by an "L" in the quality component of the Deposit Symbol.

If the Deposit Symbol shows either "C", "O", or "L" or any combination of these indicators, the quality of the deposit is considered to be reduced for some uses of the aggregate. No attempt is made to quantify the degree of limitation imposed. Assessment of the four indicators is made from published data, from data contained in files of both the Ontario Ministry of Transportation and the Engineering and Terrain Geology Section of the Ontario Geological Survey, and from field observations.

Quality data may also appear in Table 9, where the results of aggregate quality tests are listed by test type and sample location. The types of tests conducted and

the test specifications are explained in Appendixes B and E, respectively.

Analyses of unprocessed samples obtained from test holes, pits or sample sites are plotted on grain size distribution graphs. On the graphs are the Ontario Ministry of Transportation's gradation specification envelopes for aggregate products: Granular Base Course A, B and C, Hot-Laid Asphaltic Sand Nos. 1,2,3,4 and 8, and concrete sand. By plotting the gradation curves with respect to the specification envelopes, it can be determined how well the unprocessed sampled material meets the criteria for each product. These graphs, called Aggregate Grading Curves, follow the tables in the report.

Location and Setting

The location and setting of a resource area has a direct influence on its value for possible extraction. The evaluation of a deposit's setting is made on the basis of natural and man-made features which may limit or prohibit extractive development.

First, the physical context of the deposit is considered. Deposits with some physical constraint on extractive development, such as thick overburden or high water table, are less valuable resource areas because of the difficulties involved in resource recovery. Second, permanent man-made features, such as roads, railways, powerlines, and housing developments, which are built on a deposit, may prohibit its extraction. The constraining effect of legally required setbacks surrounding such features is included in the evaluation. A quantitative assessment of these constraints can be made by measurement of their areal extent directly from the topographic maps. The area rendered unavailable by these features is shown for each resource area in Table 3 (Column 3).

The assessment of sand and gravel deposits with respect to local land use and to private land ownership is an important component of the general evaluation process. These aspects of the evaluation process are not considered further in this report, but readers are encouraged to discuss them with personnel of the pertinent District Office of the Ontario Ministry of Natural Resources.

REGIONAL CONSIDERATIONS

In selecting sufficient areas for resource development, it is important to assess both the local and the regional resource base, and to forecast future production and demand patterns.

Some appreciation of future aggregate requirements in an area may be gained by assessing its present production levels and by forecasting future production trends. Such an approach is based on the assumptions that production levels in an area closely reflect the demand and that the present production "market share" of an area will remain roughly at the same level.

The aggregate resources in the region surrounding a municipality should be assessed in order to properly evaluate specific resource areas and to adopt optimum resource management plans. For example, a municipality that has large resources in comparison to its surrounding region constitutes a regionally significant resource area. Municipalities with high resources in proximity to large demand centres, such as metropolitan areas, are special cases.

Although an appreciation of the regional context is required to develop comprehensive resource management techniques, such detailed evaluation is beyond the scope of this report. The selection of resource areas made in this study is based primarily on geological data or on considerations outlined in preceding sections.

MAP 3: BEDROCK RESOURCES

Map 3 is an interpretative map derived from bedrock geology, drift thickness and bedrock topography maps, water well data from the Ontario Ministry of the Environment, oil and gas well data from the Petroleum Resources Section (Ontario Ministry of Natural Resources) and from geotechnical test hole data from various sources. Map 3 is based on concepts similar to those outlined for Maps 1 and 2, but displays both the inventory and evaluation on the one map.

The geological boundaries of the bedrock units are shown by a dashed line. Isolated outcrops are indicated by an "X". Three sets of contour lines delineate areas of less than 3 feet (1 m) of drift, areas of 3 to 25 feet (1 to 8 m) of drift, and areas of 25 to 50 feet (8 to 15 m) of drift. The extent of these areas of thin drift are shown by three shades of blue. The darkest shade indicates where bedrock outcrops or is within 3 feet (1 m) of the ground surface. These areas constitute potential resource areas because of their easy access. The medium shade indicates areas where drift cover is up to 25 feet (8 m) thick. Quarrying is possible in this depth of overburden and these zones also represent potential resource areas. The lightest shade indicates bedrock areas overlain by 25 to 50 feet (8 to 15 m) of overburden. These latter areas constitute resources which have extractive value only in specific circumstances. Outside of these delineated areas, the bedrock can be assumed to be covered by more than 50 feet (15 m) of overburden, a depth generally considered to be too great to allow economic extraction (unless part of the overburden is composed of economically attractive deposits).

Other inventory information presented on Map 3 is designed to give an indication of the present level of extractive activity in the report area. Those areas which are licenced for extraction under the Aggregate Resources Act are shown by a solid outline and identified by a number which refers to the quarry descriptions in Table 5. Each description notes the owner/operator, location, licenced acreage and an estimate of face height. Unlicenced quarries (abandoned quarries or wayside quarries operating on demand under authority of a permit) are also identified and numbered on Map 3 and

described in Table 5. Two additional symbols may appear on the map. An open dot indicates the location of a selected water well which penetrates bedrock. The overburden thickness is shown in feet beside the open dot. Similarly, test hole locations appear as a point symbol with the depth to bedrock shown in feet beside it. The test holes may be further described in Table 7.

SELECTION CRITERIA

Criteria equivalent to those used for sand and gravel deposits are used to select bedrock areas most favourable for extractive development.

The evaluation of bedrock resources is made primarily on the basis of performance and suitability data established by laboratory testing at the Ontario Ministry of Transportation. The main characteristics and uses of the bedrock units found in southern Ontario are summarized in Appendix D.

Deposit "size" is related directly to the areal extent of thin drift cover overlying favourable bedrock formations. Since vertical and lateral variations in bedrock units are much more gradual than in sand and gravel deposits, the quality and quantity of the resource are usually consistent over large areas.

Quality of the aggregate derived from specific bedrock units is established by the performance standards previously mentioned. Location and setting criteria and regional considerations are identical to those for sand and gravel deposits.

SELECTED RESOURCE AREAS

Selection of Bedrock Resource Areas has been restricted to a single level of significance. Three factors support this approach. First, quality and quantity variations are gradual. Second, the areal extent of a given quarry operation is much smaller than that of a sand and gravel pit producing an equivalent tonnage of material, and third, since crushed bedrock has a higher unit value than sand and gravel, longer haul distances can be considered. These factors allow the identification of alternative sites having similar development potential. The Selected Areas, if present, are shown on Map 3 by a line pattern and the calculated available tonnages are given in Table 6.

Selected Bedrock Resource Areas shown on Map 3 are not permanent, single land use units. They represent areas in which a major bedrock resource is known to exist and may be reserved wholly or partially for extractive development and/or resource protection.

Part III — Assessment of Aggregate Resources in St. Vincent Township

LOCATION AND POPULATION

St. Vincent Township occupies 66 342 acres (26 848 ha) in north-central Grey County, southwestern Ontario. The township is shown on portions of the Markdale (41 A/7) and Owen Sound (41 A/10) map sheets of the National Topographic System, at a scale of 1:50 000. A substantial part of the township is occupied by the Canadian Forces' Meaford Range and Training Area.

The population of the township, excluding the town of Meaford, was 1930 in 1988, an increase of 15% since 1975 (Ontario Ministry of Municipal Affairs 1991; Ontario Ministry of Treasury, Economics and Intergovernmental Affairs 1976). The majority of the inhabitants are rural-residential or farm residents. The township supports mainly farming activities, with beef and pork production being the dominant agricultural land use. Intensive agricultural specialization is carried out on the sandy soils near Meaford where approximately 2000 acres (810 ha) of land is used for apple orchards (Chapman and Putnam 1984). A large area near Meaford has been designated by the Ontario Ministry of Agriculture and Food as a specialty crop area.

The town of Meaford, which is located in the northeastern part of the township, is a local trade and retail centre. Its population was 4283 in 1988 (Ontario Ministry of Municipal Affairs 1991). There are also numerous other small unincorporated hamlets and settlements located near major road intersections and along the Nottawasaga Bay shoreline.

Access within the township is provided by King's Highway 26 as well as a grid network of paved and gravel-surfaced roads. The township is also served by a Canadian National Railways line that runs parallel to King's Highway 26 and connects Meaford to the south. The deep waters of Nottawasaga Bay have permitted the docking facilities located in Meaford.

PHYSIOGRAPHY AND SURFICIAL GEOLOGY

The surficial geology of St. Vincent Township is largely the result of glacial activity which took place during the Late Wisconsinan Substage of the Pleistocene Epoch (informally known as the "Great Ice Age"). Approximately 23 000 years ago, lobes or submasses of the Laurentide ice sheet advanced out of the basins of the Great Lakes and joined together to cover southern Ontario. The lateral extent of these ice lobes and the positions of their margins underwent numerous fluctuations until the ice receded northward. The distribution of surficial materials in St. Vincent Township is the direct and indirect result of ice margin fluctuations of the Georgian Bay ice lobe during the Late Wisconsinan Substage and postglacial events during the Holocene. Chapman and Putnam (1984) have defined four physiographic regions in St. Vincent Township. They are the Niagara Escarpment, the Bruce Peninsula, the Cape Rich steps and Bighead Valley (Chapman and Putnam 1984). A detailed geological study and mapping project of the area has been undertaken by the Ontario Geological Survey (Feenstra, in prep. a and b). The location and extent of the sand and gravel deposits in the township are shown on Maps 1 and 2 of this report.

A strong advance of the Georgian Bay ice lobe deposited a gravelly, sandy to clayey silt till over much of the township (Feenstra 1979). This till unit occurs mainly in the form of an extensively drumlinized till plain. The orientation of the drumlins indicates that the ice advance was in a southern and southeastern direction. Drumlins are particularly abundant on the sides, shoulders and floor of the Bighead Valley which is located in the southwestern part of the township. The Bighead Valley, a steep-sided re-entrant in the Niagara Escarpment, existed prior to glaciation and was further deepened by glacial erosion. The till, found throughout the township, is not acceptable for aggregate use because it contains excessive amounts of fines.

As the ice melted back from the area, ice-contact stratified drift was deposited along the ice front. A small ice-contact deposit is located in the southwestern part of St. Vincent Township. No pits have been developed in this deposit within the township.

As the ice margin melted further back, low-lying areas in the township were inundated by glacial lake waters. Glacial Lake Algonquin, which formed approximately 11 000 years ago, was the deepest lake to cover a part of this area. Approximately 5000 to 6000 years ago, when water levels lowered, the Nipissing Great Lakes were formed (Barnett and Kelly 1987). Sediments deposited in these two postglacial lakes are found near Meaford and in the vicinity of the present-day Georgian Bay and Nottawasaga Bay shorelines. Glaciolacustrine and lacustrine clay and silt were deposited in deeper or quieter water, while predominately silty fine sand was deposited in the nearshore, shallow water areas of these lakes. A large glaciolacustrine sand plain is located immediately west of Meaford. The clay, silt and sand are usually too fine grained for most construction aggregate uses. Glaciolacustrine beaches, containing mostly low quality, horizontally bedded gravel, were deposited along shorelines of the postglacial lakes in the township. The large glaciolacustrine beach deposit near Meaford, which is located at the 750 foot (229 m) above sea level elevation, was formed by glacial Lake Algonquin. This deposit contains between 8 to 12 feet (2 to 4 m) of often dirty and cobbly, fine to coarse gravel. The lower beach deposits, situated just inland from Nottawasaga Bay, at the 625 to 650 foot (190 to 198 m) elevations, were

formed by the Nipissing Great Lakes. Post-Nipissing to modern-day beach deposits occur below the 625 foot (190 m) elevation at the Nottawasaga Bay shoreline.

Postglacial erosional and depositional processes have been of some importance in modifying the physiography of St. Vincent Township. In the southeastern part of the township, the Queenston Formation is being actively eroded by creeks and, in places, gullying has produced a badland topography. Alluvial sediments are present in several locations along the banks of the Bighead River. Some sands from the glaciolacustrine plain deposits near Meaford have been redistributed by prevailing westerly winds into dunes (Feenstra 1979).

EXTRACTIVE ACTIVITY

Seventeen sand and gravel pits have been identified in St. Vincent Township. Their locations are shown on Maps 1 and 2. Many of the pits are now inactive or overgrown. At the time of writing, 4 pits were licenced for extraction under the Aggregate Resources Act. The total area of all the licenced properties in St. Vincent Township is 32.72 acres (13.24 ha).

In addition, two quarries have been opened in the township (Map 3). One quarry has been established north of Griersville in order to supplement the township's requirements for base and subbase road-building materials. The other quarry is presently abandoned, but shale has been extracted from this quarry for tile manufacture.

SELECTED SAND AND GRAVEL RESOURCE AREAS

Map 1 illustrates all of the surficial deposits which contain sand and gravel in St. Vincent Township. Unlike the aggregate-rich townships of southern Grey County, this township lacks large deposits of high quality sand and gravel. St. Vincent Township contains approximately 5400 acres (2190 ha) of sand and gravel deposits. The total estimated tonnage in these deposits is 167 million tons (152 million tonnes). Many of these deposits have limited value for aggregate extraction because of the limited amount of available aggregate and/or the poor quality of the material. Consequently, only the most significant sources are suggested for possible resource protection.

The highest quality aggregate in St. Vincent Township is generally found in the 5 glaciolacustrine beach deposits, located near Meaford (Map 2). These deposits have been grouped into one primary resource area which covers approximately 1250 acres (510 ha), exclusive of licenced properties. An estimated 890 acres (360 ha) are considered to be available for extraction, containing approximately 18 million tons (16 million tonnes) of sand and gravel.

Aggregate suitability data obtained from the Ontario Ministry of Transportation (MTO) indicate that the pits identified within Resource Area 1 generally contain aggregate suitable for base and subbase road-building materials. A major constraint affecting the quality of the aggregate in the pits is the presence of varying amounts of soft shales and calcareous siltstones. These undesirable lithologies were derived from the underlying bedrock and previously deposited glacial sediments. Clay seams and zones of cemented gravel have also been observed in several pits. Excessive fines would limit high-specification use of the material unless extensive processing was undertaken.

Samples taken from the licenced properties by staff members of the Owen Sound District Office of the Ontario Ministry of Natural Resources were analyzed for grain size distribution, soundness, absorption and lithology by the Materials Testing Laboratories of MTO in London, Ontario. The results of the tests on these samples are shown in Table 9. The specification limits for each test are included in Appendix E of this report. In general, the sampled material fell within specification limits for granular base course and 16 mm Crushed Type A products but did not meet the criteria for asphaltic and concrete stone. The presence of undesirable materials such as shale and siltstone are largely responsible for limiting the high-specification uses of the aggregate.

Selected Sand and Gravel Resource Area 1

Selected Sand and Gravel Resource Area 1 is located south and southwest of Meaford, and is oriented roughly parallel to the Nottawasaga Bay shoreline. The area consists of 5 glaciolacustrine beach deposits, labelled 1a and 1b on Map 2. Together the deposits occupy approximately 1250 acres (510 ha), exclusive of licenced properties. Numerous gravel pits have been opened in Area 1a in the past leaving substantial areas depleted. Future extractive development may be inhibited because of commercial and housing developments and because part of the area has been designated by the Ontario Ministry of Agriculture and Food as a specialty crop area.

One licenced and 11 unlicenced pits have been developed in Area 1a. Many of these pits were depleted and faces within the pits were largely overgrown or had been rehabilitated. Face heights in the pits ranged from 3 to 12 feet (1 to 4 m) and generally contained tabular units of fine to cobbly gravel, interstratified with fine to coarse sand with frequent seams of silt and clay. Estimates of gravel content ranged from 40 to 70%.

Samples of the material from pit nos. 1 and 12 contained 65 and 66% gravel, respectively (Figure 2a). Both samples were crushable because in each sample more than 20% of the material was larger than 26.5 mm in size. Pit-use data compiled from files of MTO indicate that in the past the aggregate from Area 1a has generally been acceptable for the production of Granular Base Course A, B and C, 16 mm crushed type A and B aggregate, and pit-run gravel. Although aggregate quality

data are lacking for Area 1b, the aggregate is likely to be of similar quality.

After deletions for cultural constraints and previous extraction, Selected Sand and Gravel Resource Area 1 has approximately 890 acres (360 ha) currently available for aggregate extraction. Based on an average deposit thickness of 8 feet (2 m), the deposits contain an estimated 18 million tons (16 million tonnes) of sand and gravel. The resource area is easily accessible from King's Highway 26 and various township roads.

BEDROCK GEOLOGY

St. Vincent Township is underlain by shales of the Upper Ordovician Blue Mountain, Georgian Bay and Queenston formations as well as by strata of the Lower to Middle Silurian Manitoulin, Cabot Head, Fossil Hill and Amabel formations. The distribution of, and the contacts between, the formations are shown on Map 3 (after Feenstra, in prep. a and b; Liberty and Bolton 1971). The Niagara Escarpment is the dominant geological and geomorphological feature in the area. The escarpment trends in a serrated fashion across the southern and western borders of the township. The brow of the escarpment attains a height up to 600 feet (183 m) above the floor of the Bighead River valley in the western part of the township. In this area, the escarpment consists of an upper, prominent bluff of Amabel dolostone and a lower, secondary bench of Manitoulin dolostone.

Glacial sediments which overlie the bedrock surface are generally less than 25 feet (8 m) thick, however, thicker accumulations of sediment are present in the Bighead River valley. Data from water wells north of Elmhedge indicate that more than 200 feet (61 m) of drift can overlie bedrock in the valley.

The Blue Mountain Formation, the oldest bedrock unit present in the township, has only a limited occurrence along the shore of Nottawasaga Bay near Meaford. This formation was redefined by Russell and Telford (1983), it was previously referred to as the Upper and Middle members of the Whitby Formation (Liberty and Bolton 1971). The Blue Mountain Formation consists of blue-grey, noncalcareous shale which appears suitable for use in the heavy clay products industry (Guillet 1977).

The Blue Mountain Formation is overlain by the Georgian Bay Formation which underlies much of the Bighead River valley. The formation includes alternating grey carbonate beds and grey to bluish grey shale (Liberty and Bolton 1971). The formation is over 400 feet (122 m) thick and its chemical composition is fairly consistent throughout its occurrence (Vos 1975). Georgian Bay shale is a raw material used for brick manufacture by some brick plants in southern Ontario. This shale has also been used for the production of farm drain tile and lightweight expanded aggregate (Guillet 1977). One quarry has been developed in the shale-rich lower member of the Georgian Bay Formation near Meaford (quarry no. 2). Shale was extracted from a 20- to 25-foot (6 to 8 m) face for the manufacture of farm drain tile.

The Queenston Formation overlies the Georgian Bay Formation and consists predominately of red shale with occasional beds of mottled green shale (Liberty and Bolton 1971). The Queenston shales underlie a considerable area of the township and are exposed in numerous stream valleys. Southeast of Meaford, the shales are severely eroded with numerous ravines creating a topography that resembles the badlands of arid climates. There are many areas of the Queenston Formation in the southeastern and northern part of the township that are thinly covered by drift. Although the Queenston shale is a resource of provincial significance for the production of structural clay products, it is relatively carbonate-rich in the southern Georgian Bay area (Feenstra, in prep. b). Carbonate-rich shale is generally undesirable in brick or tile manufacture.

The Queenston Formation is overlain by the grey and bluish grey, thin- to medium-bedded, fine-grained dolomitic limestone and dolostone of the Manitoulin Formation. Shale partings and lenses of white chert are known to occur within this limestone (Vos 1969). Outcrops are common and the formation is well exposed at a roadcut located west of Kiowana Beach. Dolostone from the Manitoulin Formation is currently quarried at a site located north of Griersville in the southern part of the township (quarry no. 1). The quarry face exposes 10 to 20 feet (3 to 6 m) of mottled grey and bluish grey, thin- to thick-bedded, fine- to medium-crystalline dolostone. The dolostone is used for base and subbase road-building aggregates. Areas underlain by the Manitoulin Formation have not been selected for possible resource protection because of its inferior quality with respect to the Amabel Formation. These areas of Manitoulin Formation, however, lie outside the Niagara Escarpment Commission planning area and thus may become more attractive for development.

The maroon and green noncalcareous shale and calcareous carbonate beds of the Cabot Head Formation overlie the Manitoulin Formation and form much of the face of the Niagara Escarpment. The thickness of the formation in the area ranges from 37 to 135 feet (11 to 41 m) (Liberty and Bolton 1971). The shale is too soft for use as load-bearing aggregate. The formation is generally suitable for use as expanded aggregate, brick and tile, but it has not been used for these purposes because exposures suitable for quarrying are scarce (Vos 1969). The Cabot Head shale has not been selected for possible resource protection in St. Vincent Township because of its limited extent and poor exposures.

The Cabot Head Formation is overlain by the thin-bedded, brown, medium-crystalline, fossiliferous dolostone of the Fossil Hill Formation. The thickness of the formation varies from 6 to 15 feet (2 to 5 m) in this area, and is of very limited extent (Feenstra, in prep. b). Since exposures of the Fossil Hill dolostone are very limited along the face of the escarpment, the formation

has been grouped together with the overlying Amabel Formation on Map 3.

The erosion resistant Amabel Formation dolostone forms the caprock of the Niagara Escarpment and underlies areas located in the southern and western parts of the township. The formation within the township largely consists of fine-crystalline dolostone, although minor amounts of porous, medium- to coarse-crystalline dolostone and patchy occurrences of thin-bedded, dark brown, bituminous dolostone also occur (Bolton 1957; Liberty and Bolton 1971). Minor quantities of chert may also be present, especially near the base of the formation. Another characteristic of the Amabel Formation is the abundance of large reef structures. These reefs can be 50 to 60 feet (15 to 18 m) high and a few hundred feet in diameter (Hewitt 1960).

Those areas of the Amabel Formation that are overlain by less than 25 feet (8 m) of drift in the township have been selected for possible resource protection. The Amabel Formation is a provincially significant aggregate source and is suitable for the production of a wide range of industrial mineral products including crushed stone, concrete aggregate, building stone and as raw material for lime manufacture. Several characteristics of the Amabel Formation may, however, affect the use of the stone for aggregate. If chert is present in high quantities, it may limit the use of the dolostone to low-grade aggregate products. Another limitation is the presence of reef structures. The reef rock may not be as suitable for some aggregate uses as nonreefal rock because the reef rock is generally more porous and absorptive, probably softer and less durable, and may contain clay pockets and iron staining, particularly near the surface. Extraction difficulties may also occur because of the mound-like form of these reefs and the steeply dipping beds flanking the reefs (Hewitt 1960).

Selected Bedrock Resource Areas 1 and 2

Selected Bedrock Resource Areas 1 and 2 consist of all those areas where the Amabel Formation dolostone is overlain by less than 25 feet (8 m) of glacial sediments. The Amabel dolostone is usually of high quality, however, porous reefal structures and chert, where encountered, may restrict some high-specification uses of the aggregate. For these reasons, the quality of the bedrock should be investigated at sites proposed for quarry development prior to extraction. A significant thickness of Amabel dolostone may be suitable for quarrying as exposures of up to 40 feet (12 m) can be observed along the brow of the escarpment (Vos 1969).

The Selected Bedrock Resource Areas have a combined area of 2700 acres (1090 ha), of which 2550 acres (1030 ha) are presently available for extraction. Assuming an average workable thickness of 60 feet (18 m), available bedrock resources are estimated to be approximately 560 million tons (510 million tonnes). Considerable portions of the selected areas lie within policy areas of the Niagara Escarpment Commission and may be unavailable for future extractive development. The resource areas are easily accessible by King's Highway 26 and numerous paved county and township roads. A Canadian National Railways line runs parallel with Highway 26 which connects Meaford to the south.

SUMMARY

The sand and gravel deposits of St. Vincent Township are the products of glacial processes which took place during the Late Wisconsinan Substage of the Pleistocene Epoch. The sand and gravel deposits in the township consist of thin accumulations of ice-contact stratified drift, beach and glaciolacustrine sediments. Five glaciolacustrine beach deposits have been selected at the primary level of significance. The aggregate from these deposits is suitable for base and subbase road-building materials. However, only limited amounts of material may be available for extraction from Resource Area 1 because: 1) part of the Area is located in an area designated by the Ontario Ministry of Agriculture and Food as a specialty crop area, 2) there are existing land use pressures and 3) there has been previous aggregate extraction. The sand and gravel resources presently available will probably be insufficient to meet local needs in the future.

The township is underlain by Late Ordovician to Middle Silurian age shales and dolostones. The Amabel Formation, which is the caprock of the Niagara Escarpment, is considered to be the most suitable for extractive development. The high quality Amabel dolostone can be used for the production of a wide range of crushed stone and industrial mineral products. Several areas (Bedrock Resource Areas 1a to 1d and 2a to 2e) of thinly drift-covered Amabel dolostone have been selected for possible resource protection. The availability of these bedrock resources may be restricted because they lie within the policy areas of the Niagara Escarpment Commission. A quarry has been opened in the Manitoulin Formation to supplement the township's requirements for base and subbase road-building materials.

Enquiries regarding the Aggregate Resources Inventory of St. Vincent Township may be directed to the Aggregate Assessment Office, Engineering and Terrain Geology Section, Ontario Geological Survey, Ministry of Northern Development and Mines at the 7th Floor, 77 Grenville Street, Toronto, Ontario, M7A 1W4 [Tel. (416) 965-1663], or to the Resident Geologist, Ministry of Northern Development and Mines, Box 5463, 659 Exeter Road, London, Ontario, N6A 4L6 [Tel. (519) 661-2796] or to the Owen Sound District Office, Ministry of Natural Resources, 611 9th Avenue East, Owen Sound, Ontario, N4K 3E4 [Tel. (519) 376-3860].

TABLE 1. TOTAL SAND AND GRAVEL RESOURCES, ST. VINCENT TOWNSHIP*.

1 CLASS NO.	2 DEPOSIT TYPE (see Appendix C)	3 AREAL EXTENT Acres (Hectares)	4 ORIGINAL TONNAGE Millions of Tons (Tonnes)	1 CLASS NO.	2 DEPOSIT TYPE (see Appendix C)	3 AREAL EXTENT Acres (Hectares)	4 ORIGINAL TONNAGE Millions of Tons (Tonnes)
2	S–LB	25 (10)	< 1 (< 1)		S–LB	400 (162)	8 (7)
	S–LP	3550 (1440)	133 (121)	4	S–LB	110 (45)	1 (1)
3	G–LB	1260 (510)	25 (23)		S–LP	65 (26)	< 1 (< 1)
	S–IC	5 (2)	< 1 (< 1)	**TOTAL FOR REPORT AREA:**		5400 (2190)	167 (152)

** Identified deposit areas within the town of Meaford and the Canadian Forces' Meaford Range and Training Area have been omitted on all tables.*

N.B. Minor variations in all tables are caused by rounding of data.

TABLE 2. SAND AND GRAVEL PITS, ST. VINCENT TOWNSHIP.

1 NO.	2 MTO NO.	3 OWNER/ OPERATOR	4 LOT	5 CONC.	6 LICENCED AREAS Acres (Hectares)	7 FACE HEIGHT Feet (Metres)	8 % GRAVEL
Licenced Pits							
1	O6-12	Lavor Contracting Ltd.	18	9	11.4 (4.6)	-	rehabilitated
2	-	B. Murrary	Pt.17	7	5.56 (2.25)	10-15 (3-5)	< 30-40
3	-	B. Murray Contracting	Pt.15	7	14.33 (5.8)	< 10 (< 3)	sand
4	-	B. Murray	Pt.12	5	1.43 (0.58)	<6 (< 2)	overgrown
TOTAL LICENCED AREA:					32.72 (13.24)		
Unlicenced Pits*							
5	-	Unknown	25	7	-	10-20 (3-6)	. sand partially overgrown
6	O6-57	Unknown	19	8	-	5-10 (1.5-3)	40 overgrown
7	O6-04	Johnson	19	8	-	10 (3)	waterfilled, overgrown
8	O6-23	Juniper	18	8	-	12 (4)	depleted, overgrown
9	O6-37	Lambe	17	8	-	10 (3)	50-60 partially overgrown
10	O6-63	Gillespie	4	4	-	10-20 (3-6)	sand
11	O6-18	J.Foster	16	8	-	8-10 (2-3)	60-70
12	-	H.Sutherland Construction Ltd.	15	7&8	-	6-12 (2-4)	60-70
13	O6-52	Cramp	13	7	-	3-10 (1-3)	40-60
14	-	Unknown	13	16	-	<5 (< 1.5)	waterfilled
15	-	Unknown	13	6	-	5-8 (1.5-2)	40-60
16	-	Unknown	13	6	-	<5 (< 1.5)	variable
17	O6-16	Allan	12	6	-	5-10 (1.5-3)	variable

** Abandoned pits or wayside pits operating on demand under authority of a permit.*

TABLE 3. SELECTED SAND AND GRAVEL RESOURCE AREAS, ST. VINCENT TOWNSHIP.

1 **DEPOSIT NO.**	2 **UNLICENCED AREA** Acres (Hectares)	3 **CULTURAL SETBACKS** Acres (Hectares)	4 **EXTRACTED AREA** Acres (Hectares)	5 **AVAILABLE AREA** Acres (Hectares)	6 **ESTIMATED DEPOSIT THICKNESS** Feet (Metres)	7 **AVAILABLE AGGREGATE** Millions of Tons (Tonnes)
1a	1040 (420)	170 (69)	110 (45)	760 (310)	8 (2)	15 (14)
1b	210 (85)	80 (32)	0 (0)	130 (53)	8 (2)	3 (3)
TOTAL FOR REPORT AREA:	1250 (510)	250 (101)	110 (45)	890 (360)		18 (16)

TABLE 4. TOTAL IDENTIFIED BEDROCK RESOURCES, ST. VINCENT TOWNSHIP.

1 DRIFT THICKNESS Feet (Metres)	2 FORMATION	3 ESTIMATED DEPOSIT THICKNESS Feet (Metres)	4 AREAL EXTENT Acres (Hectares)	5 ORIGINAL TONNAGE Millions of Tons (Tonnes)
0–3 (0–1)	Amabel & Fossil Hill	60 (18)	2600 (1050)	560 (510)
3–25 (1–8)	Amabel & Fossil Hill	60 (18)	100 (40)	22 (20)
25–50 (8–15)	Amabel & Fossil Hill	60 (18)	18 (7)	4 (4)
			2700 (1090)	590 (540)
0–3 (0–1)	Cabot Head	60 (18)	125 (51)	24 (22)
3–25 (1–8)	Cabot Head	60 (18)	300 (121)	58 (53)
25–50 (8–15)	Cabot Head	60 (18)	25 (10)	5 (4)
			450 (182)	87 (79)
0–3 (0–1)	Manitoulin	40 (12)	1900 (770)	275 (249)
3–25 (1–8)	Manitoulin	40 (12)	2140 (870)	310 (280)
25–50 (8–15)	Manitoulin	40 (12)	1140 (460)	164 (149)
			5200 (2100)	750 (680)
0–3 (0–1)	Queenston	60 (18)	7000 (2850)	1340 (1220)
3–25 (1–8)	Queenston	60 (18)	3300 (1340)	630 (570)
25–50 (8–15)	Queenston	60 (18)	3200 (1300)	610 (550)
			13 500 (5500)	2600 (2360)
0–3 (0–1)	Georgian Bay	60 (18)	350 (142)	67 (61)
3–25 (1–8)	Georgian Bay	60 (18)	3750 (1520)	720 (650)
25–50 (8–15)	Georgian Bay	60 (18)	1850 (750)	355 (320)
			6000 (2430)	1140 (1030)
3–25 (1–8)	Blue Mountain	60 (18)	110 (44)	21 (19)
TOTAL FOR REPORT AREA:			28 000 (11 300)	5200 (4700)

TABLE 5. QUARRIES, ST. VINCENT TOWNSHIP.

1 NO.	2 MTO NO.	3 OWNER/ OPERATOR	4 LOT	5 CONC.	6 LICENCED AREA Acres (Hectares)	7 FACE HEIGHT Feet (Metres)
Licenced Quarries						
1	O6-73	Sutherland	5	5	56.24 (22.76)	10-20 (3-6)
Unlicenced Quarries*						
2	-	Bauman	Pt.12	3	-	20-25 (6-8)

** Abandoned quarries or wayside quarries operating on demand under authority of a permit.*

TABLE 6. SELECTED BEDROCK RESOURCE AREAS, ST. VINCENT TOWNSHIP.

1 DEPOSIT NO.	2 DEPTH OF OVERBURDEN Feet (Metres)	3 UNLICENCED AREA Acres (Hectares)	4 CULTURAL SETBACKS Acres (Hectares)	5 EXTRACTED AREA Acres (Hectares)	6 AVAILABLE AREA Acres (Hectares)	7 ESTIMATED WORKABLE THICKNESS Feet (Metres)	8 AVAILABLE RESOURCES Millions of Tons (Tonnes)
1a	0-3 (0-1)	2130 (860)	100 (40)	0 (0)	2030 (820)	60 (18)	440 (400)
1b	0-3 (0-1)	265 (107)	0 (0)	0 (0)	265 (107)	60 (18)	57 (52)
1c	0-3 (0-1)	12 (5)	5 (2)	0 (0)	7 (3)	60 (18)	2 (2)
1d	0-3 (0-1)	200 (81)	25 (10)	0 (0)	175 (71)	60 (18)	38 (34)
		2600 (1050)	130 (53)	0 (0)	2480 (1000)		540 (490)
2a	3-25 (1-8)	10 (4)	2 (1)	0 (0)	8 (3)	60 (18)	2 (2)
2b	3-25 (1-8)	25 (10)	0 (0)	0 (0)	25 (10)	60 (18)	5 (5)
2c	3-25 (1-8)	30 (12)	10 (4)	0 (0)	20 (8)	60 (18)	4 (4)
2d	3-25 (1-8)	10 (4)	5 (2)	0 (0)	5 (2)	60 (18)	1 (1)
2e	3-25 (1-8)	25 (10)	0 (0)	0 (0)	25 (10)	60 (18)	5 (5)
		100 (40)	17 (7)	0 (0)	83 (34)		17 (15)
TOTAL FOR REPORT AREA:		2700 (1090)	147 (59)	0 (0)	2550 (1030)		560 (510)

TABLE 7. SUMMARY OF TEST HOLE DATA, ST. VINCENT TOWNSHIP.

Test Hole Number: SV-1H-1

Location: St. Vincent Township, Town of Meaford

Elevation: 596 feet (182 m) asl

Source: Johnson et al. (1983), Well Log CL6D No. 17.

Depth feet (metres)	Description
0–10 (0–3)	overburden
10–170 (3–52)	Blue Mountain Formation; shale
	10–87 ft (3–27 m) – light greenish grey shale; partly fissile; infrequent fossils; pyrite present.
	87–107 ft (27–52 m) – green and brown mottled shale becoming increasingly brownish grey towards the base; thin silty lens in the lowest metre.
170–176 (52–54)	Lindsay Formation (Collingwood Member); very dark brown to black shale; petroliferous odour; numerous bioclastic beds; lower 8–12 inches (20–30 cm) consist of medium brown, calcareous shale.
176–180 (54–55)	Lindsay Formation; buff grey, micro-crystalline limestone with a more argillaceous bed near the top.
180 (55)	end of core

TABLE 8. SUMMARY OF GEOPHYSICS DATA, ST. VINCENT TOWNSHIP.

- N O N E -

TABLE 9. RESULTS OF AGGREGATE QUALITY TESTS, ST. VINCENT TOWNSHIP.

	COARSE AGGREGATE				FINE AGGREGATE
	Petrographic Number				
Sample No.	Granular & 16 mm Crushed	Hot Mix & Concrete	Magnesium Sulphate Soundness (% Loss)	Absorption (%)	Magnesium Sulphate Soundness (% Loss)
Pit 1	143	219	6	2.1	12
Pit 12	160	247	8	2.0	14
Quarry 1	108	138	6	2.1	-
Quarry 1	100	113	5	2.1	-

NOTE: The quality test data refers strictly to a specific sample. Because of the inherent variability of sand and gravel deposits, care should be exercised in extrapolating such information to the rest of the deposit.



FIGURE 2a. AGGREGATE GRADING CURVES, ST. VINCENT TOWNSHIP.

Based on analysis of the total aggregate contained in unprocessed samples (gradation envelopes adapted from M T O Form 1010, 1980).

NOTE:

Information portrayed by grading curves refers strictly to a specific sample at the time of field investigation. Due to the inherent variability of sand and gravel deposits care should be exercised in extrapolating such information to the rest of the deposit.



FIGURE 2b. AGGREGATE GRADING CURVES, ST. VINCENT TOWNSHIP.

Based on analysis of the sand fraction of the aggregate contained in unprocessed samples (gradation envelopes adapted from MTO Forms 1002, 1979 and 1003, 1981).

NOTE:

Information portrayed by grading curves refers strictly to a specific sample taken at the time of field investigation. Due to the inherent variability of sand and gravel deposits care should be exercised in extrapolating such information to the rest of the deposit.

References

Association of Professional Engineers of Ontario 1976. Performance standards for professional engineers advising on and reporting on oil, gas and mineral properties; Association of Professional Engineers of Ontario, 11p.

Barnett, P.J. and Kelly, R.I. 1987. XIIth INQUA Congress Field Excursion A-11, Quaternary history of southern Ontario; National Research Council of Canada, 77p.

Bolton, T.E. 1957. Silurian stratigraphy and paleontology of the Niagara Escarpment in Ontario; Geological Survey of Canada, Memoir 289, 145p.

Chapman, L.J. and Putnam, D.F. 1984. The physiography of southern Ontario, 3rd ed.; Ontario Geological Survey, Special Volume 2, 270p.

Feenstra, B.H. 1979. Quaternary geology of the Owen Sound area, Grey County; *in* Summary of Field Work 1979, Ontario Geological Survey, Miscellaneous Paper 90, p.133-134.

——in preparation a. Quaternary geology of the Owen Sound area, Grey County; Ontario Geological Survey.

——in preparation b. Quaternary geology of the Markdale area, Grey County; Ontario Geological Survey.

Guillet, G.R. 1977. Clay and shale deposits of Ontario; Ontario Geological Survey, Mineral Deposits Circular 15, 117p.

Hewitt, D.F. 1960. The limestone industries of Ontario; Ontario Department of Mines, Industrial Mineral Circular 5, 117p.

Johnson, M.D., Russell, D.J. and Telford, P.G. 1983. Oil shale assessment project, volume 1, shallow drilling results 1981/82; Ontario Geological Survey, Open File Report 5458, 36p.

Liberty, B.A. 1966. Geology of the Bruce Peninsula, Ontario; Geological Survey of Canada, Paper 65-41, 8p.

Liberty, B.A. and Bolton, T.E. 1971. Paleozoic geology of the Bruce Peninsula area, Ontario; Geological Survey of Canada, Memoir 360, 163p.

Ontario Interministerial Committee on National Standards and Specifications (Metric Committee) 1975. Metric practice guide; 67p.

Ontario Ministry of Municipal Affairs 1991. Municipal directory 1991; Queen's Printer for Ontario, 226p.

Ontario Ministry of Northern Development and Mines 1989. 1988 Ontario mineral score; Ontario Ministry of Northern Development and Mines, 218p.

Ontario Ministry of Treasury, Economics and Intergovernmental Affairs 1976. 1976 municipal directory; Queen's Printer for Ontario, 175p.

Robertson, J.A. 1975. Mineral deposit studies, mineral potential evaluation and regional planning in Ontario; Ontario Division of Mines, Miscellaneous Paper 61, 42p.

Russell, D.J. and Telford, P.G. 1983. Revisions to the stratigraphy of the Upper Ordovician Collingwood beds of Ontario - a potential oil shale; Canadian Journal of Earth Sciences, v.20, no.12, p.1780-1790.

Vos, M.A. 1969. Stone resources of the Niagara Escarpment; Ontario Department of Mines, Industrial Mineral Report 31, 68p.

——1975. Potential clay and shale resources of central Ontario; Ontario Division of Mines, Open File Report 5133, 40p.

Appendix A — Suggested Additional Reading

Banerjee, I. and McDonald, B.C. 1975. Nature of esker sedimentation; *in* Glaciofluvial and Glaciolacustrine Sedimentation, Society of Economic Paleontologists and Mineralogists, Special Paper no. 23, p.132-154.

Bates, R.L. and Jackson, J.A. eds. 1987. Glossary of geology, 3rd ed.; American Geological Institute, Alexandria, 788p.

Bauer, A.M. 1970. A guide to site development and rehabilitation of pits and quarries; Ontario Department of Mines, Industrial Mineral Report 33, 62p.

Cowan, W.R. 1977. Toward the inventory of Ontario's mineral aggregates; Ontario Geological Survey, Miscellaneous Paper 73, 19p.

Fairbridge, R.W. ed. 1968. The encyclopedia of geomorphology; Encyclopedia of Earth Sciences, v.3, Reinhold Book Corp., New York, 1295p.

Flint, R.F. 1971. Glacial and Quaternary geology; John Wiley and Sons Inc., New York, 892p.

Guillet, G.R. and Joyce, I.H. 1987. The clay and shale industries of Ontario; Ontario Ministry of Natural Resources, 157p.

Derry Michener Booth and Wahl and Ontario Geological Survey 1989a. Limestone industries of Ontario, volume I – geology, properties and economics; Ontario Ministry of Natural Resources, Land Management Branch, 158p.

——1989b. Limestone industries of Ontario, volume II – limestone industries and resources of eastern and northern Ontario; Ontario Ministry of Natural Resources, Land Management Branch, 196p.

——1989c. Limestone industries of Ontario, volume III – limestone industries and resources of central and southwestern Ontario; Ontario Ministry of Natural Resources, Land Management Branch, 175p.

Hewitt, D.F. 1964a. Building stones of Ontario, part I introduction; Ontario Department of Mines, Industrial Mineral Report 14, 43p.

——1964b. Building stones of Ontario, part II limestone; Ontario Department of Mines, Industrial Mineral Report 15, 43p.

——1964c. Building stones of Ontario, part III marble; Ontario Department of Mines, Industrial Mineral Report 16, 89p.

——1964d. Building stones of Ontario, part IV sandstone; Ontario Department of Mines, Industrial Mineral Report 17, 57p.

——1972. Paleozoic geology of southern Ontario; Ontario Division of Mines, Geological Report 105, 18p.

Hewitt, D.F. and Karrow, P.F. 1963. Sand and gravel in southern Ontario; Ontario Department of Mines, Industrial Mineral Report 11, 151p.

Hewitt, D.F. and Vos, M.A. 1970. Urbanization and rehabilitation of pits and quarries; Ontario Department of Mines, Industrial Mineral Report 34, 21p.

Lowe, S.B. 1980. Trees and shrubs for the improvement and rehabilitation of pits and quarries in Ontario; Ontario Ministry of Natural Resources, 71p.

McLellan, A.G., Yundt, S.E. and Dorfman, M.L. 1979. Abandoned pits and quarries in Ontario; Ontario Geological Survey, Miscellaneous Paper 79, 36p.

Michalski, M.F.P., Gregory, D.R. and Usher, A.J. 1987. Rehabilitation of pits and quarries for fish and wildlife; Ontario Ministry of Natural Resources, Land Management Branch, 59p.

Ontario Mineral Aggregate Working Party 1977. A policy for mineral aggregate resource management in Ontario; Ontario Ministry of Natural Resources, 232p.

Ontario Ministry of Natural Resources 1975. Vegetation for the rehabilitation of pits and quarries; Forest Management Branch, Division of Forests, 38p.

Peat, Marwick and Partners and M.M. Dillon Limited 1981a. Mineral aggregate transportation study; Industrial Mineral Background Paper 1, 133p.

——1981b. Mineral aggregate transportation study; Industrial Mineral Background Paper 1a, 26p.

Proctor and Redfern Limited 1974. Mineral aggregate study, central Ontario planning region; prepared for the Ontario Ministry of Natural Resources, 200p.

Proctor and Redfern Limited and Gartner Lee Associates Limited 1975. Mineral aggregate study and geological inventory of part of the eastern Ontario region; prepared for the Ontario Ministry of Natural Resources, 326p.

——1977. Mineral aggregate study and geological inventory, southwestern region of Ontario; prepared for the Ontario Ministry of Natural Resources, 246p.

Rogers, C.A. 1985a. Alkali aggregate reactions, concrete aggregate testing and problem aggregates in Ontario–a review, 5th revised ed.; Ontario Ministry of Transportation and Communications, Engineering Materials Office, Report EM-31, 44p.

——1985b. Evaluation of the potential for expansion and cracking due to the alkali–carbonate reaction; *in* Cement, Concrete and Aggregates, CCAGDP, v.8, no.1, p.13-23.

Appendix B — Glossary

Abrasion resistance: Tests such as the Los Angeles abrasion test are used to measure the ability of aggregate to resist crushing and pulverizing under conditions similar to those encountered in processing and use. Measuring resistance is an important component in the evaluation of the quality and prospective uses of aggregate. Hard, durable material is preferred for road building.

Absorption capacity: Related to the porosity of the rock types of which an aggregate is composed. Porous rocks are subject to disintegration when absorbed liquids freeze and thaw, thus decreasing the strength of the aggregate.

Aggregate: Any hard, inert, construction material (sand, gravel, shells, slag, crushed stone or other mineral material) used for mixing in various-sized fragments with a cement or bituminous material to form concrete, mortar, etc., or used alone for road building or other construction. Synonyms include mineral aggregate and granular material.

Aggregate Abrasion Value: This test directly measures the resistance of aggregate to abrasion with silica sand and a steel disk. The higher the value, the lower the resistance to abrasion. For high quality asphalt surface course uses, values of less than 6 are desirable.

Alkali-aggregate reaction: A chemical reaction between the alkalies of Portland cement and certain minerals found in rocks used for aggregate. Alkali-aggregate reactions are undesirable because they can cause expansion and cracking of concrete. Although perfectly suitable for building stone and asphalt applications, alkali-reactive aggregates should be avoided for structural concrete uses.

Beneficiation: Beneficiation of aggregates is a process or combination of processes which improves the quality (physical properties) of a mineral aggregate and is not part of the normal processing for a particular use, such as routine crushing, screening, washing or classification. Heavy media separation, jigging, or application of special crushers (e.g., "cage mill") are usually considered processes of beneficiation.

Blending: Required in cases of extreme coarseness, fineness, or other irregularities in the gradation of unprocessed aggregate. Blending is done with approved sand-sized aggregate in order to satisfy the gradation requirements of the material.

Bulk Relative Density: An aggregate with low relative density is lighter in weight than one with a high relative density. Low relative density aggregates (less than about 2.5) are often non-durable for many aggregate uses.

Cambrian: The first period of the Paleozoic Era, thought to have covered the time between 570 and 500 million years ago. The Cambrian precedes the Ordovician Period.

Clast: An individual constituent, grain or fragment of a sediment or rock, produced by the mechanical weathering of a larger rock mass. Synonyms include particle and fragment.

Crushable aggregate: Unprocessed gravel containing a minimum of 35% coarse aggregate larger than the No. 4 sieve (4.75 mm) as well as a minimum of 20% greater than the 26.5 mm sieve.

Deleterious lithology: A general term used to designate those rock types which are chemically or physically unsuited for use as construction or road-building aggregates. Such lithologies as chert, shale, siltstone and sandstone may deteriorate rapidly when exposed to traffic and other environmental conditions.

Devonian: A period of the Paleozoic Era thought to have covered the span of time between 395 and 345 million years ago, following the Silurian Period. Rocks formed in the Devonian Period are among the youngest found in Ontario.

Dolostone: A carbonate sedimentary rock consisting chiefly of the mineral dolomite and containing relatively little calcite (dolostone is also known as dolomite).

Drift: A general term for all unconsolidated rock debris transported from one place and deposited in another, distinguished from underlying bedrock. In North America, glacial activity has been the dominant mode of transport and deposition of drift. Synonyms include overburden and surficial deposit.

Drumlin: A low, smoothly rounded, elongated hill, mound, or ridge composed of glacial materials. These landforms were formed beneath an advancing ice sheet, and were shaped by its flow.

Eolian: Pertaining to the wind, especially with respect to landforms whose constituents were transported and deposited by wind activity. Sand dunes are an example of an eolian landform.

Fines: A general term used to describe the size fraction of an aggregate which passes (is finer than) the No. 200 mesh screen (0.075 mm). Also described informally as "dirt", these particles are in the silt and clay size range.

Glacial lobe: A tongue-like projection from the margin of the main mass of an ice cap or ice sheet. During the Pleistocene Epoch several lobes of the Laurentide continental ice sheet occupied the Great Lakes basins. These lobes advanced then melted back numerous times during the Pleistocene, producing the complex arrangement of glacial material and landforms found in southern Ontario.

Gradation: The proportion of material of each particle size, or the frequency distribution of the various sizes which constitute a sediment. The strength, durability,

permeability and stability of an aggregate depend to a great extent on its gradation. The size limits for different particles are as follows:

Boulder	more than 200 mm
Cobbles	75-200 mm
Coarse Gravel	26.5-75 mm
Fine Gravel	4.75-26.5 mm
Coarse Sand	2-4.75 mm
Medium Sand	0.425-2 mm
Fine Sand	0.075-0.425 mm
Silt, Clay	less than 0.075 mm

Granular base course: Components of the pavement structure of a road, which are placed on the subgrade and are designed to provide strength, stability and drainage, as well as support for surfacing materials. Several types have been defined: Granular Base Course A consists of crushed and processed aggregate and has relatively stringent quality standards in comparison to Granular Base Course B and C which are usually pit-run or other unprocessed aggregate.

Hot-laid (or asphaltic) aggregate: Bituminous, cemented aggregates used in the construction of pavements either as surface or bearing course (HL 1, 3 and 4), or as binder course (HL 2 and 8) used to bind the surface course to the underlying granular base course.

Lithology: The description of rocks on the basis of such characteristics as colour, structure, mineralogic composition and grain size. Generally, the description of the physical character of a rock.

Los Angeles Abrasion and Impact Test: This test measures the resistance to abrasion and the impact strength of aggregate. This gives an idea of the breakdown that can be expected to occur when an aggregate is stockpiled, transported and placed. Values less than about 35% indicate potentially satisfactory performance for most concrete and asphalt uses. Values of more than 45% indicate that the aggregate may be susceptible to excessive breakdown during handling and placing.

Magnesium sulphate soundness test: This test is designed to simulate the action of freezing and thawing on aggregates. Those aggregates which are susceptible to freezing and thawing will usually break down and give high losses in this test. Values greater than about 12 to 15% indicate potential problems for concrete and asphalt coarse aggregate.

Meltwater channel: A drainage way, often terraced, produced by water flowing away from a melting glacier margin.

Ordovician: An early period of the Paleozoic Era thought to have covered the span of time between 500 and 435 million years ago.

Paleozoic era: One of the major divisions of the geologic time scale thought to have covered the time between 570 and 230 million years ago, the Paleozoic Era (or Ancient Life Era) is subdivided into six geologic periods, of which only four (Cambrian, Ordovician, Silurian and Devonian) can be recognized in southern Ontario.

Petrographic examination: Individual aggregate particles in a sample are divided into categories good, fair, poor, and deleterious, based on their rock type (petrography) and knowledge of past field performance. A petrographic number (PN) is calculated. The higher the PN, the lower the quality of the aggregate.

Pleistocene: An epoch of the recent geological past including the time from approximately 2 million years ago to 7000 years ago. Much of the Pleistocene was characterized by extensive glacial activity and is popularly referred to as the "Great Ice Age".

Polished Stone Value: This test measures the frictional properties of aggregates after 6 hours of abrasion and polishing with an emery abrasive. The higher the PSV, the higher the frictional properties of the aggregate. Values less than 45 indicate marginal frictional properties, while values greater than 55 indicate excellent frictional properties.

Possible resource: Reserve estimates based largely on broad knowledge of the geological character of the deposit and for which there are few, if any, samples or measurements. The estimates are based on assumed continuity or repetition for which there are reasonable geological indications.

Precambrian: The earliest geological period extending from the consolidation of the earth's crust to the beginning of the Cambrian.

Shale: A fine-grained, sedimentary rock formed by the consolidation of clay, silt or mud and characterized by well developed bedding planes, along which the rock breaks readily into thin layers. The term shale is also commonly used for fissile claystone, siltstone and mudstone.

Silurian: An early period of the Palezoic Era thought to have covered the time between 435 and 395 million years ago. The Silurian follows the Ordovician Period and precedes the Devonian Period.

Soundness: The ability of the components of an aggregate to withstand the effects of various weathering processes and agents. Unsound lithologies are subject to disintegration caused by the expansion of absorbed solutions. This may seriously impair the performance of road-building and construction aggregates.

Till: Unsorted and unstratified rock debris, deposited directly by glaciers, and ranging in size from clay to large boulders.

Wisconsinan: Pertaining to the last glacial period of the Pleistocene Epoch in North America. The Wisconsinan began approximately 100 000 years ago and ended approximately 7000 years ago. The glacial deposits and landforms of southern Ontario are predominantly the result of glacial activity during the Wisconsinan Stage.

Appendix C — Geology of Sand and Gravel Deposits

The type, distribution, and extent of sand and gravel deposits in southern Ontario are the result of extensive glacial and glacially influenced activity in Wisconsinan time during the Pleistocene Epoch, approximately 100 000 to 7000 years ago. The deposit types reflect the different depositional environments that existed during the melting and retreat of the continental ice masses, and can readily be differentiated on the basis of their morphology, structure, and texture. The deposit types are described below.

GLACIOFLUVIAL DEPOSITS

These deposits can be divided into two broad categories: those that were formed in contact with (or in close proximity to) glacial ice, and those that were deposited by meltwaters carrying materials beyond the ice margin.

Ice-Contact Terraces (ICT): These are glaciofluvial features deposited between the glacial margin and a confining topographic high, such as the side of a valley. The structure of the deposits may be similar to that of outwash deposits, but in most cases the sorting and grading of the material is more variable and the bedding is discontinuous because of extensive slumping. The probability of locating large amounts of crushable aggregate is moderate, and extraction may be expensive because of the variability of the deposits both in terms of quality and grain size distribution.

Kames (K): Kames are defined as mounds of poorly sorted sand and gravel deposited by meltwater in depressions or fissures on the ice surface or at its margin. During glacial retreat, the melting of supporting ice causes collapse of the deposits, producing internal structures characterized by bedding discontinuities. The deposits consist mainly of irregularly bedded and cross-bedded, poorly sorted sand and gravel. The present forms of the deposits include single mounds, linear ridges (crevasse fillings) or complex groups of landforms. The latter are occasionally described as "undifferentiated ice-contact stratified drift" (IC) when detailed subsurface information is unavailable. Since kames commonly contain large amounts of fine-grained material and are characterized by considerable variability, there is generally a low to moderate probability of discovering large amounts of good quality, crushable aggregate. Extractive problems encountered in these deposits are mainly the excessive variability of the aggregate and the rare presence of excess fines (silt- and clay-sized particles).

Eskers (E): Eskers are narrow, sinuous ridges of sand and gravel deposited by meltwaters flowing in tunnels within or at the base of glaciers, or in channels on the ice surface. Eskers vary greatly in size. Many, though not all eskers, consist of a central core of poorly sorted and stratified gravel characterized by a wide range in grain size. The core material is often draped on its flanks by better sorted and stratified gravel. The deposits have a high probability of containing a large proportion of crushable aggregate, and since they are generally built above the surrounding ground surface, are convenient extraction sites. For these reasons esker deposits have been traditional aggregate sources throughout Ontario, and are significant components of the total resources of many areas.

Some planning constraints and opportunities are inherent in the nature of the deposits. Because of their linear nature, the deposits commonly extend across several property boundaries leading to unorganized extractive development at numerous small pits. On the other hand, because of their form, eskers can be easily and inexpensively extracted and are amenable to rehabilitation and sequential land use.

Undifferentiated Ice-Contact Stratified Drift (IC): This designation may include deposits from several ice-contact, depositional environments which usually form extensive, complex landforms. It is not feasible to identify individual areas of coarse-grained material within such deposits because of their lack of continuity and grain size variability. They are given a qualitative rating based on existing pit and other subsurface data.

Outwash (OW): Outwash deposits consist of sand and gravel laid down by meltwaters beyond the margin of the ice lobes. The deposits occur as sheets or as terraced valley fills (valley trains) and may be very large in extent and thickness. Well developed outwash deposits have good horizontal bedding and are uniform in grain size distribution. Outwash deposited near the glacier's margin is much more variable in texture and structure. The probability of locating useful crushable aggregates in outwash deposits is moderate to high depending on how much information on size, distribution and thickness is available.

Subaqueous Fan (SF): Subaqueous fans are formed within or near the mouths of meltwater conduits when sediment laden meltwaters are discharged into a standing body of water. The geometry of the resulting deposit is fan or lobe shaped. Several of these lobes may be joined together to form a larger, continuous sedimentary body. Internally, subaqueous fans consist of stratified sands and gravels which may exhibit wide variations in grain size distribution. As these features were deposited under glacial lake waters, silt and clay which settled out of these lakes may be associated in varying amounts with these deposits. The variability of the sediments and presence of fines are the main extractive problems associated with these deposits.

Alluvium (AL): Alluvium is a general term for clay, silt, sand, gravel, or similar unconsolidated material deposited during postglacial time by a stream as sorted or semi-sorted sediment, on its bed or on its floodplain. The probability of locating large amounts of crushable aggregate in alluvial deposits is low, and they have

generally low value because of the presence of excess silt- and clay-sized material. There are few large post-glacial alluvium deposits in Ontario.

GLACIOLACUSTRINE DEPOSITS

Glaciolacustrine Beach Deposits (LB): These are relatively narrow, linear features formed by wave action at the shores of glacial lakes that existed at various times during the deglaciation of southern Ontario. Well developed lacustrine beaches are usually less than 20 feet (6 m) thick. The aggregate is well sorted and stratified and sand-sized material commonly predominates. The composition and size distribution of the deposit depends on the nature of the source material. The probability of obtaining crushable aggregate is high when the material is developed from coarse-grained materials such as a stony till, and low when developed from fine-grained materials. Beaches are relatively narrow, linear deposits, so that extractive operations are often numerous and extensive.

Glaciolacustrine Deltas (LD): These features were formed where streams or rivers of glacial meltwater flowed into lakes and deposited their suspended sediment. In southern Ontario such deposits tend to consist mainly of sand and abundant silt. However, in near-ice and ice-contact positions, coarse material may be present. Although deltaic deposits may be large, the probability of obtaining coarse material is generally low.

Glaciolacustrine Plains (LP): The nearly level surface marking the floor of an extinct glacial lake. The sediments which form the plain are predominantly fine to medium sand, silt, and clay, and were deposited in relatively deep water. Lacustrine deposits are generally of low value as aggregate sources because of their fine grain size and lack of crushable material. In some aggregate-poor areas, lacustrine deposits may constitute valuable sources of fill and some granular base course aggregate.

GLACIAL DEPOSITS

End Moraines (EM): These are belts of glacial drift deposited at, and parallel to, glacier margins. End moraines commonly consist of ice-contact stratified drift and in such instances are usually called kame moraines. Kame moraines commonly result from deposition between two glacial lobes (interlobate moraines). The probability of locating aggregates within such features is moderate to low. Exploration and development costs are high. Moraines may be very large and contain vast aggregate resources, but the location of the best areas within the moraine is usually poorly defined.

EOLIAN DEPOSITS

Windblown Deposits (WD): Windblown deposits are those formed by the transport and deposition of sand by winds. The form of the deposits ranges from extensive, thin layers to well developed linear and crescentic ridges known as dunes. Most windblown deposits in southern Ontario are derived from, and deposited on, pre-existing lacustrine sand plain deposits. Windblown sediments almost always consist of fine to coarse sand and are usually well sorted. The probability of locating crushable aggregate in windblown deposits is very low.

Appendix D — Geology of Bedrock Deposits

The purpose of this appendix is to familiarize the reader with the general bedrock geology of southern Ontario (Figure D1), and the potential uses of the various bedrock formations where known. The reader is cautioned against using this information for more specific purposes. The stratigraphic chart (Figure D2) is intended only to illustrate the stratigraphic sequences in particular geographic areas and should not be used as a regional correlation table.

The following description is arranged in ascending stratigraphic order, on a group and formation basis. Precambrian rocks are not discussed. Additional stratigraphic information is included for some formations where necessary. The publications and maps of the Ontario Geological Survey and the Geological Survey of Canada should be referred to for more detailed information. The composition, thickness, and uses of the formations are discussed. If a formation may be suitable for use as aggregate and aggregate suitability test data is available, the data has been included in the form of ranges. The following short forms have been used in presenting this data: PSV = Polished Stone Value, AAV = Aggregate Abrasion Value, $MgSO_4$ = Magnesium Sulphate Soundness Test (loss in percent), LA = Los Angeles Abrasion and Impact Test (loss in percent), Absn = Absorption (percent), BRD = Bulk Relative Density, PN (Asphalt & Concrete) = Petrographic Number for Asphalt and Concrete use.

The ranges are intended as a guide only and care should be exercised in extrapolating the information to specific situations. Aggregate suitability test data has been provided by the Ontario Ministry of Transportation.

Covey Hill Formation (Cambrian)

STRATIGRAPHY: lower formation of the Potsdam Group. COMPOSITION: interbedded non-calcareous feldspathic conglomerate and sandstone. THICKNESS: 0 to 45 feet (0 to 14 m). USES: has been quarried for aggregate in South Burgess Township, Leeds County.

Nepean Formation (Cambro-Ordovician)

STRATIGRAPHY: upper formation of the Potsdam Group. COMPOSITION: thin-bedded to massive quartz sandstone with some conglomerate interbeds and rare shaly partings. THICKNESS: 0 to 100 feet (0 to 30 m). USES: suitable as dimension stone; quarried at Philipsville and Forfar for silica sand; alkali-silica reactive in Portland cement concrete. AGGREGATE SUITABILITY TESTING: PSV = 54-68, AAV = 4-15, $MgSO_4$ = 9-32, LA = 44-90, Absn = 1.6-2.6, BRD = 2.38-2.50, PN (Asphalt & Concrete) = 130-140.

March Formation (Lower Ordovician)

STRATIGRAPHY: lower formation of the Beekmantown Group. COMPOSITION: interbedded quartz sandstone, dolomitic quartz sandstone, sandy dolostone and dolostone. THICKNESS: 60 to 197 feet (18 to 60 m). USES: quarried extensively for aggregate in area of subcrop and outcrop; alkali-silica reactive in Portland cement concrete; lower part of formation is an excellent source of skid-resistant aggregate; suitable for use as facing stone and paving stone. AGGREGATE SUITABILITY TESTING: PSV = 55-60, AAV = 4-6, $MgSO_4$ = 1-17, LA = 15-38, Absn = 0.5-0.9, BRD = 2.61-2.65, PN (Asphalt & Concrete) = 110-150.

Oxford Formation (Lower Ordovician)

STRATIGRAPHY: upper formation of the Beekmantown Group. COMPOSITION: thin- to thick-bedded, microcrystalline to medium-crystalline, grey dolostone with thin shaly interbeds. THICKNESS: 200 to 335 feet (61 to 102 m). USES: quarried in the Brockville and Smith Falls areas and south of Ottawa for use as aggregate. AGGREGATE SUITABILITY TESTING: PSV = 47-48, AAV = 7-8, $MgSO_4$ = 1-4, LA = 18-23, Absn = 0.7-0.9, BRD = 2.74-2.78, PN (Asphalt & Concrete) = 105-120.

Rockcliffe Formation (Middle Ordovician)

STRATIGRAPHY: divided into lower member and upper (St. Martin) member. COMPOSITION: interbedded quartz sandstone and shale; interbedded shaly bioclastic limestone and shale predominating in upper member to the east. THICKNESS: 0 to 410 feet (0 to 125 m). USES: upper member has been quarried east of Ottawa for aggregate; lower member has been used as crushed stone; some high purity limestone beds in upper member may be suitable for use as fluxing stone and in lime production. AGGREGATE SUITABILITY TESTING: PSV = 58-63, AAV = 10-11, $MgSO_4$ = 12-40, LA = 25-28, Absn = 1.8-1.9, BRD = 2.55-2.62, PN (Asphalt & Concrete) = 122-440.

Shadow Lake Formation (Middle Ordovician)

STRATIGRAPHY: eastern Ontario - the basal unit of the Ottawa Group; central Ontario - overlain by the Simcoe Group. COMPOSITION: in eastern Ontario - silty and sandy dolostone with shale partings and minor interbeds of sandstone; in central Ontario - conglomer-

ates, sandstones, and shales. THICKNESS: eastern Ontario - 7 to 10 feet (2 to 3 m); central Ontario - 0 to 40 feet (0 to 12 m). USES: potential source of decorative stone; very limited value as aggregate source.

Gull River Formation (Middle Ordovician)

STRATIGRAPHY: part of the Simcoe Group (central Ontario) and Ottawa Group (eastern Ontario). In central and eastern Ontario the formation is subdivided into upper and lower members; west of Lake Simcoe it is presently subdivided into upper, middle and lower members. COMPOSITION: in central and eastern Ontario the lower member consists of alternating units of limestone, dolomitic limestone, and dolostone, the upper member consists of thin-bedded limestones with thin shale partings; west of Lake Simcoe the lower member is thin- to thick-bedded, interbedded, grey argillaceous limestone and buff to green dolostone, whereas the upper and middle members are dense microcrystalline limestones with argillaceous dolostone interbeds. THICKNESS: 23 to 204 feet (7 to 62 m). USES: quarried in the Lake Simcoe, Kingston, Ottawa, and Cornwall areas for crushed stone; rock from certain layers in eastern and central Ontario has proven to be alkali-reactive when used in Portland cement concrete (alkali-carbonate reaction). AGGREGATE SUITABILITY TESTING: PSV = 41-49, AAV = 8-12, $MgSO_4$ = 3-13, LA = 18-28, Absn = 0.3-0.9, BRD = 2.68-2.73, PN (Asphalt & Concrete) = 100-153.

Bobcaygeon Formation (Middle Ordovician)

STRATIGRAPHY: part of the Simcoe Group (central Ontario) and the Ottawa Group (eastern Ontario), subdivided into upper, middle and lower members; members in eastern and central Ontario are approximately equivalent. COMPOSITION: homogeneous, massive to thin-bedded fine-crystalline limestone with numerous shaly partings in the middle member. THICKNESS: 80 to 285 feet (24 to 87 m). USES: quarried at Brechin, Marysville, and in the Ottawa area for crushed stone; generally suitable for use as granular base course aggregate; rock from certain layers has been found to be alkali-reactive when used in Portland cement concrete (alkali-silica reaction). AGGREGATE SUITABILITY TESTING: PSV = 47-51, AAV = 14-23, $MgSO_4$ = 1-40, LA = 18-32, Absn = 0.3-2.4, BRD = 2.5-2.69, PN (Asphalt & Concrete) = 100-320.

Verulam Formation (Middle Ordovician)

STRATIGRAPHY: part of Simcoe and Ottawa Groups. COMPOSITION: fossiliferous, pure to argillaceous limestone interbedded with calcareous shale. THICKNESS: 105 to 230 feet (32 to 70 m). USES: quarried at Picton and Bath for use in cement manufacture; quarried for aggregate in Mara Township, Simcoe County and in the Belleville-Kingston area; may be unsuitable for use as aggregate in some areas because of its high shale content. AGGREGATE SUITABILITY TESTING: PSV = 43-44, AAV = 9-13, $MgSO_4$ = 4-45, LA = 22-29, Absn = 0.4-2.1, BRD = 2.59-2.70, PN (Asphalt & Concrete) = 120-255.

Lindsay Formation (Middle and Upper Ordovician)

STRATIGRAPHY: part of Simcoe and Ottawa Groups; in eastern Ontario is divisible into an unnamed lower member and the Eastview Member; in central Ontario is divisible into the Collingwood Member (equivalent to portions of the Eastview Member) and a lower member. COMPOSITION: in eastern Ontario the lower member is interbedded, very fine- to coarse-crystalline limestone with undulating shale partings and interbeds of dark grey calcareous shale, whereas the Eastview Member is an interbedded dark grey to dark brown calcareous shale and very fine- to fine-crystalline, petroliferous limestone; in central Ontario Collingwood Member is a black, calcareous shale whereas the lower member is a very fine- to coarse-crystalline, thin-bedded limestone with very thin, undulating shale partings. THICKNESS: 82 to 200 feet (25 to 61 m). USES: in eastern Ontario the lower member is used extensively for aggregate production; in central Ontario it is quarried at Picton, Ogden Point and Bowmanville for cement; may be suitable or unsuitable for use as concrete and asphalt aggregate. AGGREGATE SUITABILITY TESTING: $MgSO_4$ = 2-47, LA = 20-28, Absn = 0.4-1.3, BRD = 2.64-2.70, PN (Asphalt & Concrete) = 110-215.

Blue Mountain and Billings Formations (Upper Ordovician)

STRATIGRAPHY: central Ontario - Blue Mountain Formation includes the upper and middle members of the former Whitby Formation; eastern Ontario - Billings Formation is equivalent to part of the Blue Mountain Formation. COMPOSITION: the Blue Mountain Formation is blue-grey, noncalcareous shale; Billings Formation is dark grey to black, noncalcareous to slightly calcareous, pyritiferous shale with dark grey limestone laminae and grey siltstone interbeds. THICKNESS: Blue Mountain Formation - 140 to 200 feet (43 to 61 m); Billings Formation - 0 to 205 feet (0 to 62 m). USES: Billings Formation may be a suitable source for structural clay products and expanded aggregate; Blue Mountain Formation may be suitable for structural clay products.

Georgian Bay and Carlsbad Formations (Upper Ordovician)

COMPOSITION: in central Ontario the Georgian Bay Formation is composed of interbedded limestone and shale; in eastern Ontario the Carlsbad Formation is composed of interbedded shale, siltstone and bioclastic limestone; THICKNESS: Georgian Bay Formation is 300 to 560 feet (91 to 170 m); Carlsbad Formation - 0 to 610 feet (0 to 186 m). USES: Georgian Bay Formation is

used by several producers in Metropolitan Toronto area to produce brick and structural tile, as well as for making Portland cement; at Streetsville, expanded shale was used in the past to produce lightweight aggregate; Carlsbad Formation is used as a source material for brick and tile manufacturing, has potential as a lightweight expanded aggregate.

Queenston Formation (Upper Ordovician)

COMPOSITION: red, thin- to thick-bedded, sandy to argillaceous shale with green mottling and banding. THICKNESS: 400 to 500 feet (122 to 152 m). USES: there are several large quarries developed in the Queenston Formation in the Toronto-Hamilton region and one at Russell, near Ottawa; all extract shale for brick manufacturing; the Queenston Formation is the most important source material for brick manufacture in Ontario.

Whirlpool Formation (Lower Silurian)

STRATIGRAPHY: lower formation in the Cataract Group in the Niagara Penninsula and the Niagara Escarpment as far north as Duntroon. COMPOSITION: massive, medium- to coarse-grained, argillaceous white to light grey quartz sandstone with thin grey shale partings. THICKNESS: 0 to 25 feet (0 - 8 m). USES: building stone, flagstone.

Manitoulin Formation (Lower Silurian)

STRATIGRAPHY: part of the Cataract Group, occurs north of Stoney Creek. COMPOSITION: thin-bedded, blue-grey to buff-brown dolomitic limestones and dolostones. THICKNESS: 0 to 75 feet (0 to 23 m). USES: extracted for crushed stone in St. Vincent Township, Grey County, and for decorative stone on Manitoulin Island. AGGREGATE SUITABILITY TESTING: no data.

Cabot Head Formation (Lower Silurian)

STRATIGRAPHY: part of the Cataract Group, occurs throughout southern Ontario, south and north of the Niagara Escarpment. COMPOSITION: green, grey and red shales. THICKNESS: 50 to 60 feet (15 to 18 m); USES: potential source of coated lightweight aggregate and raw material for use in manufacture of brick and tile; lack of suitable exposures has limited its use.

Grimsby Formation

STRATIGRAPHY: upper formation of the Cataract Group, is identified on the Niagara Peninsula as far north as Clappison's Corners. COMPOSITION: interbedded sandstone and shale, mostly red. THICKNESS: 0 to 50 feet (0 to 15 m). USES: no present uses.

Thorold Formation (Middle Silurian)

STRATIGRAPHY: lower formation in the Clinton Group on the Niagara Peninsula. COMPOSITION: thick-bedded quartz sandstone. THICKNESS: 7 to 10 feet (2 - 3 m). USES: no present uses.

Neagha Formation (Middle Silurian)

STRATIGRAPHY: part of the Clinton Group on the Niagara Peninsula. COMPOSITION: dark grey to green shale with minor interbedded limestone. THICKNESS: 0 to 5 feet (0 to 2 m). USES: no present uses.

Dyer Bay Formation (Middle Silurian)

STRATIGRAPHY: lower formation in the Clinton Group on Manitoulin Island and northernmost Bruce Peninsula. COMPOSITION: highly fossiliferous, impure dolostone. THICKNESS: 0 to 20 feet (0 to 6 m). USES: no present uses.

Wingfield Formation (Middle Silurian)

STRATIGRAPHY: part of the Clinton Group on Manitoulin Island and northernmost Bruce Peninsula. COMPOSITION: olive green to grey shale with dolostone interbeds. THICKNESS: 0 to 36 feet (0 to 11 m). USES: no present uses.

St. Edmund Formation (Middle Silurian)

STRATIGRAPHY: part of the Clinton Group on Manitoulin Island and northernmost Bruce Peninsula, upper portion previously termed the Mindemoya Formation. COMPOSITION: pale grey to buff brown, micro- to medium-crystalline, thin- to medium-bedded dolostone. THICKNESS: 0 to 85 feet (0 to 26 m). USES: quarried for fill and crushed stone on Manitoulin Island. AGGREGATE SUITABILITY TESTING: $MgSO_4$ = 1-2, LA = 19-21, Absn = 0.6-0.7, BRD = 2.78-2.79, PN (Asphalt & Concrete) = 105.

Fossil Hill and Reynales Formations (Middle Silurian)

STRATIGRAPHY: part of Clinton Group; Fossil Hill Formation occurs in the northern part of the Niagara Escarpment and is approximately equivalent in part, to the Reynales Formation which occurs on the Niagara Peninsula and the Escarpment, as far north as the Forks of the Credit. COMPOSITION: Fossil Hill Formation is fine- to coarse-crystalline dolostone with high silica content; Reynales Formation is thin- to thick-bedded shaly dolostone and dolomitic limestone. THICKNESS: Fossil Hill Formation - 20 to 85 feet (6 to 26 m); Reynales Formation - 0 to 10 feet (0 to 3 m). USES: both formations quarried for aggregate with overlying Amabel and Lockport Formations. AGGREGATE SUITABILITY TESTING: (Fossil Hill Formation on Manitoulin Island) $MgSO_4$ = 41, LA = 29, Absn = 4.1, BRD = 2.45, PN (Asphalt & Concrete) = 370.

Irondequoit Formation (Middle Silurian)

STRATIGRAPHY: part of Clinton Group on the Niagara Peninsula south of Waterdown. COMPOSITION: massive, coarse-crystalline crinoidal limestone. THICKNESS: 0 to 7 feet (0 to 2 m). USES: not significantly utilized.

Rochester Formation (Middle Silurian)

STRATIGRAPHY: part of Clinton Group along the Niagara Peninsula. COMPOSITION: black to dark grey calcareous shale with numerous limestone lenses. THICKNESS: 15 to 60 feet (5 to 18 m). USES: not significantly utilized. AGGREGATE SUITABILITY TESTING: PSV = 69, AAV = 17, $MgSO_4$ = 95, LA = 19, Asbn = 2.2, BRD = 2.67, PN (Asphalt & Concrete) = 400.

Decew Formation (Middle Silurian)

STRATIGRAPHY: part of Clinton Group south of Waterdown along the Niagara Peninsula. COMPOSITION: sandy to shaly dolomitic limestone and dolostone. THICKNESS: 0 to 15 feet (0 to 5 m). USES: too shaly for high quality uses, but is quarried along with Lockport Formation in places. AGGREGATE SUITABILITY TESTING: PSV = 67, AAV = 15, $MgSO_4$ = 55, LA = 21, Absn = 2.2, BRD = 2.66, PN (Asphalt & Concrete) = 255.

Lockport and Amabel Formations (Middle Silurian)

STRATIGRAPHY: Lockport Formation occurs from Waterdown to Niagara Falls, subdivided into 3 formal members: Gasport, Goat Island and Eramosa Members and an informal member (the "Vinemount shale beds"); the stratigraphically equivalent Amabel Formation, found from Waterdown to Cockburn Island, is subdivided into Lions Head, Wiarton/Colpoy Bay, and Eramosa members. COMPOSITION: Lockport Formation is thin- to massive-bedded, fine- to medium-crystalline dolostone; Amabel Formation is thin bedded to massive, medium-crystalline dolostone with reef facies near Georgetown and on the Bruce Peninsula. THICKNESS: (Lockport/ Amabel) 10 to 130 feet (3 to 40 m). USES: both formations have been used to produce lime, crushed stone, concrete aggregate, and building stone throughout their area of occurrence, and are a resource of provincial significance. AGGREGATE SUITABILITY TESTING: PSV = 36-49, AAV = 10-17, $MgSO_4$ = 2-6, LA = 25-32, Absn = 0.4-1.54, BRD = 2.61-2.81, PN (Asphalt & Concrete) = 100-105.

Guelph Formation (Middle Silurian)

STRATIGRAPHY: exposed on the Niagara Escarpment from the Niagara River to the tip of the Bruce Peninsula, mostly present in the subsurface of southwestern Ontario. COMPOSITION: micro-crystalline to medium-crystalline, thick-bedded, soft, porous dolostone, characterized in places by extensive vuggy, porous reefal facies of high chemical purity. THICKNESS: 100 to 170 feet (30 to 52 m). USES: some areas appear soft and unsuitable for use in the production of load-bearing aggregate; this unit requires additional testing to fully establish its aggregate suitability; main use is for dolomitic lime for cement manufacture; quarried near Hamilton and Guelph.

Salina Formation (Upper Silurian)

STRATIGRAPHY: present in the subsurface of southwestern Ontario; rarely exposed at the surface. COMPOSITION: grey and maroon shale, brown dolostone and, in places, salt, anhydrite and gypsum; consists predominantly of evaporitic rich material with up to eight units identifiable. THICKNESS: 370 to 600 feet (113 to 183 m). USES: gypsum mines at Hagersville, Caledonia, and Drumbo; salt is mined at Goderich and Windsor, and is produced from brine wells at Amherstburg, Windsor and Sarnia.

Bertie and Bass Islands Formations (Upper Silurian)

STRATIGRAPHY: Bertie Formation found in southern Niagara Peninsula; Bass Islands Formation, the Michigan Basin equivalent of the Bertie Formation, does not significantly outcrop in Ontario but is present in the subsurface in southwestern Ontario; Bertie Formation represented by Oatka, Falkirk, Scajaquanda, Williamsville, and Akron Members. COMPOSITION: medium- to massive-bedded, micro-crystalline, brown dolostone with shaly partings. THICKNESS: 45 to 160 feet (14 to 49 m). USES: quarried for crushed stone on the Niagara Peninsula at Fort Erie, Cayuga, Hagersville and Dunnville; shaly intervals are unsuitable for use as high specification aggregate because of low freeze-thaw durability; has also been extracted for lime. AGGREGATE SUITABILITY TESTING: PSV = 46-49, AAV = 8-11, $MgSO_4$ = 4-19, LA = 14-23, Absn = 0.8-2.8, BRD = 2.61-2.78, PN (Asphalt & Concrete) = 102-120.

Oriskany Formation (Lower Devonian)

STRATIGRAPHY: basal Devonian clastic unit, found in Niagara Peninsula. COMPOSITION: thick- to massive-bedded, coarse-grained, grey-yellow sandstone. THICKNESS: 0 to 15 feet (0 to 5 m). USES: has been quarried for silica sand, building stone, and armour stone; may be acceptable for use as rip rap, and well cemented varieties may be acceptable for some asphaltic products. AGGREGATE SUITABILITY TESTING: (of a well cemented variety of the formation) PSV = 64, AAV = 6, $MgSO_4$ = 2, LA = 29, Absn = 1.2-1.3, BRD = 2.55, PN (Asphalt & Concrete) = 107.

Bois Blanc Formation (Lower Devonian)

STRATIGRAPHY: Springvale Sandstone Member forms the lower portion of formation. COMPOSITION: a cherty limestone with shale partings and minor interbedded dolostones; Springvale Sandstone Member is a medium- to coarse-grained, green glauconitic sandstone with interbeds of limestone, dolostone and brown chert. THICKNESS: 10 to 130 feet (3 to 40 m). USES: quarried at Hagersville, Cayuga, and Port Colborne for crushed stone; material generally unsuitable for concrete aggregate because of high chert content. AGGREGATE SUITABILITY TESTING: PSV = 48-53, AAV = 3-7, $MgSO_4$ = 3-18, LA = 15-22, Absn = 1.3-2.8, BRD = 2.50-2.70, PN (Asphalt & Concrete) = 102-290.

Onondaga Formation (Middle Devonian)

STRATIGRAPHY: correlated to part of the Detroit River Group; occurs on the Niagara Peninsula from Simcoe to Niagara Falls; contains the Edgecliff, Clarence, and Moorehouse Members. COMPOSITION: medium-bedded, fine- to coarse-grained, dark grey-brown or purplish-brown, variably cherty limestone. THICKNESS: 60 to 82 feet (18 to 25 m) USES: quarried for crushed stone on the Niagara Peninsula at Welland and Port Colborne; high chert content makes much of the material unsuitable for use as concrete aggregate and asphaltic concrete; has been used as a raw material in cement manufacture. AGGREGATE SUITABILITY TESTING: (Clarence and Edgecliff Members) $MgSO_4$ = 1-6, LA = 16.8-22.4, Absn = 0.5-1.1, PN (Asphalt & Concrete) = 190-276.

Amherstburg Formation (Middle Devonian)

STRATIGRAPHY: part of Detroit River Group; correlated to Onondaga Formation in Niagara Penninsula; contains Sylvania Sandstone Member and Formosa Reef Limestone. COMPOSITION: bituminous, bioclastic, stromatoporoid-rich limestone and dolostone with grey chert nodules; Formosa Reef Limestone is high purity (calcium rich) limestone; Sylvania Sandstone Member is quartz sandstone. THICKNESS: 0 to 165 feet (0 to 50 m); Formosa Reef Limestone up to 85 feet (26 m). USES: cement manufacture, agricultural lime, aggregate. AGGREGATE SUITABILITY TESTING: PSV = 57, AAV = 19, $MgSO_4$ = 9-35, LA = 26-52, Absn = 1.1-6.4, BRD = 2.35-2.62, PN (Asphalt & Concrete) = 105-300.

Lucas Formation (Middle Devonian)

STRATIGRAPHY: part of the Detroit River Group in southwestern Ontario; includes the Anderdon Member which, in the Woodstock Beachville area, may constitute the bulk of the formation. COMPOSITION: light brown or grey-brown dolostone with bituminous laminations and minor chert; Anderdon Member consists of very high purity (calcium-rich) limestone. THICKNESS: 130 to 246 feet (40 to 75 m). USES: most important source of high-purity limestone in Ontario; used as calcium lime for metallurgical flux and for the manufacture of chemicals; rock of lower purity is used for cement manufacture, agricultural lime and aggregate; Anderdon Member is quarried at Amherstburg for crushed stone. AGGREGATE SUITABILITY TESTING: PSV = 46-47, AAV = 15-16, $MgSO_4$ = 2-60, LA = 22-47, Absn = 1.1-6.5, BRD = 2.35-2.40, PN (Asphalt & Concrete) = 110-160.

Dundee Formation (Middle Devonian)

STRATIGRAPHY: few natural outcrops, largely in the subsurface of southwestern Ontario. COMPOSITION: fine- to medium-crystalline, brownish-grey, medium- to thick-bedded, dolomitic limestone with shaly partings sandy layers, and chert in some areas. THICKNESS: 50 to 100 feet (15 to 30 m). USES: quarried near Port Dover and on Pelee Island for crushed stone; used at St. Marys as a raw material for Portland cement. AGGREGATE SUITABILITY TESTING: $MgSO_4$ = 1-28, LA = 22-46, Absn = 0.6-6.8, PN (Asphalt & Concrete) = 125-320.

Marcellus Formation (Middle Devonian)

STRATIGRAPHY: subsurface unit, mostly found below Lake Erie and extending into the eastern U.S.A., pinches out in the Port Stanley area. COMPOSITION: black, bituminous shales. THICKNESS: 0 to 15 feet (0 to 5 m). USES: no present uses.

Bell Formation (Middle Devonian)

STRATIGRAPHY: lowest formation of the Hamilton Group, no outcrop in Ontario. COMPOSITION: soft blue and grey calcareous shale. THICKNESS: 0 to 30 feet (0 to 9 m). USES: no present uses.

Rockport Quarry Formation (Middle Devonian)

STRATIGRAPHY: part of the Hamilton Group; no outcrop in Ontario. COMPOSITION: grey-brown, very fine-grained limestone with occasional shale layers. THICKNESS: 0 to 20 feet (0 to 6 m). USES: no present uses.

Arkona Formation (Middle Devonian)

STRATIGRAPHY: part of the Hamilton Group. COMPOSITION: blue-grey, plastic, clay shale with occasional thin and laterally discontinuous limestone lenses. THICKNESS: 15 to 120 feet (5 to 37 m). USES: has been extracted at Thedford and near Arkona for the production of drainage tile.

Hungry Hollow Formation (Middle Devonian)

STRATIGRAPHY: part of the Hamilton Group. COMPOSITION: grey crinoidal limestone and soft, fossiliferous calcareous shale. THICKNESS: 0 to 6 feet (0 to 2 m). USES: suitable for some crushed stone and fill with selective quarrying. AGGREGATE SUITABILITY TESTING: No data.

Widder Formation (Middle Devonian)

STRATIGRAPHY: part of the Hamilton Group. COMPOSITION: mainly soft, grey, fossiliferous calcareous shale interbedded with blue-grey, fine-grained fossiliferous limestone. THICKNESS: 0 to 45 feet (0 to 14 m). USES: no present uses.

Ipperwash Formation (Middle Devonian)

STRATIGRAPHY: upper formation of the Hamilton Group; very limited distribution. COMPOSITION: medium- to coarse-grained, grey-brown, bioclastic limestone. THICKNESS: 5 to 45 feet (2-14 m). USES: no present uses.

Kettle Point Formation (Upper Devonian)

STRATIGRAPHY: occurs in a band between Sarnia and Erieau; small part overlain by Port Lambton Group rocks in extreme northwest. COMPOSITION: black, highly fissile, organic-rich shale with minor interbeds of grey-green silty shale. THICKNESS: 0 to 200 feet (0 to 61 m). USES: possible source of fill; possible source of material for use as sintered lightweight aggregate.

Bedford Formation (Upper Devonian)

STRATIGRAPHY: lower formation of the Port Lambton Group. COMPOSITION: soft, grey shale. THICKNESS: 0 to 108 feet (0 to 33 m). USES: no present uses.

Berea Formation (Upper Devonian)

STRATIGRAPHY: middle formation of the Port Lambton Group; not known to occur at surface in Ontario. COMPOSITION: grey, fine- to medium-grained sandstone, often dolomitic and interbedded with grey shale and siltstone. THICKNESS: 0 to 197 feet (0 to 60 m). USES: no present uses.

Sunbury Formation (Upper Devonian)

STRATIGRAPHY: upper formation of the Port Lambton Group; not known to occur at surface in Ontario. COMPOSITION: black shale. THICKNESS: 0 to 66 feet (0 to 20 m). USES: no present uses.



Figure D1. Bedrock Geology of Southern Ontario.



Figure D2. Exposed Paleozoic Stratigraphic Sequences in Southern Ontario
(adapted from: Bezys, R. K., and Johnson, M.D. 1988. The geology of the Paleozoic formations utilized by the limestone industry of Ontario; The Canadian Mining and Metallurgical Bulletin v.81, no.912, p.49–58).

Appendix E — Aggregate Quality Test Specifications

Four types of aggregate quality tests are often performed by the Ontario Ministry of Transportation on sampled material. A description of Table E1 and the specification limits for each test are given in this appendix. Although a specific sample meets or does not meet the specification limits for a certain product, it may or may not be acceptable for that use based on field performance. Additional quality tests other than the four major tests listed in this appendix can be used to determine the suitability of an aggregate. The tests are performed by the Soils and Aggregates Section, Engineering Materials Office, Ontario Ministry of Transportation.

Absorption capacity: Related to the porosity of the rock types of which an aggregate is composed. Porous rocks are subject to disintegration when absorbed liquids freeze and thaw, thus decreasing the strength of the aggregate.

Los Angeles abrasion and impact test: This test measures the resistance to abrasion and the impact strength of aggregate. This gives an idea of the breakdown that can be expected to occur when an aggregate is stockpiled, transported, and placed. Values less than about 35% indicate potentially satisfactory performance for most concrete and asphalt uses. Values of more than 45% indicate that the aggregate may be susceptible to excessive breakdown during handling and placing.

Magnesium sulphate soundness test: This test is designed to simulate the action of freezing and thawing on aggregates. Those aggregates which are susceptible to freezing and thawing will usually break down and give high losses in this test. Values greater than about 12 to 15% indicate potential problems for concrete and asphalt coarse aggregate.

Petrographic examination: Individual aggregate particles in a sample are divided into categories good, fair, poor, and deleterious, based on their rock type (petrography) and knowledge of past field performance. A petrographic number (PN) is calculated. The higher the PN, the lower the quality of the aggregate.

TABLE E1. SELECTED QUALITY REQUIREMENTS FOR MAJOR AGGREGATE PRODUCTS.

	TYPE OF TEST				
	COARSE AGGREGATE				FINE AGGREGATE
TYPE OF MATERIAL	Petrographic Number Maximum	Magnesium Sulphate Soundness Maximum % Loss	Absorption Maximum %	Los Angeles Abrasion Maximum % Loss	Magnesium Sulphate Soundness Maximum % Loss
Granular Base A	200	–	–	60	–
16 mm Crushed Type 'A'	160	–	–	35	–
16 mm Crushed Type 'B'	200	–	–	60	–
Granular Subbase B	250	–	–	–	–
Granular Subbase C	250	–	–	–	–
Granular Subbase D	–	–	–	–	–
Hot Mix – HL 1	100	5	1.0	15	16
Hot Mix – HL 2	–	–	–	–	20
Hot Mix – HL 3	135	12	1.75	35	16
Hot Mix – HL 4	160	12	2.0	35	20
Hot Mix – HL 8	160	15	2.0	35	20
Structural Concrete and Concrete Base	140	12	2.0	35	16
Pavement Concrete and Exposed Structure Deck	125	12	2.0	35	16

(Ministry of Transportation Forms 1002, 1003 and 1010)

CONVERSION FACTORS FOR MEASUREMENTS IN ONTARIO GEOLOGICAL SURVEY PUBLICATIONS

Conversion from SI to Imperial			Conversion from Imperial to SI		
SI Unit	*Multiplied by*	*Gives*	*Imperial Unit*	*Multiplied by*	*Gives*
		LENGTH			
1 mm	0.039 37	inches	1 inch	**25.4**	mm
1 cm	0.393 70	inches	1 inch	**2.54**	cm
1 m	3.280 84	feet	1 foot	**0.304 8**	m
1 m	0.049 709 7	chains	1 chain	20.116 8	m
1 km	0.621 371	miles (statute)	1 mile (statute)	**1.609 344**	km
		AREA			
1 cm^2	0.155 0	square inches	1 square inch	**6.451 6**	cm^2
1 m^2	10.763 9	square feet	1 square foot	**0.092 903 04**	m^2
1 km^2	0.386 10	square miles	1 square mile	2.589 988	km^2
1 ha	2.471 054	acres	1 acre	0.404 685 6	ha
		VOLUME			
1 cm^3	0.061 02	cubic inches	1 cubic inch	**16.387 064**	cm^3
1 m^3	35.314 7	cubic feet	1 cubic foot	0.028 316 85	m^3
1 m^3	1.308 0	cubic yards	1 cubic yard	0.764 555	m^3
		CAPACITY			
1 L	1.759 755	pints	1 pint	0.568 261	L
1 L	0.879 877	quarts	1 quart	1.136 522	L
1 L	0.219 969	gallons	1 gallon	**4.546 090**	L
		MASS			
1 g	0.035 273 96	ounces (avdp)	1 ounce (avdp)	28.349 523	g
1 g	0.032 150 75	ounces (troy)	1 ounce (troy)	**31.103 476 8**	g
1 kg	2.204 62	pounds (avdp)	1 pound (avdp)	**0.453 592 37**	kg
1 kg	0.001 102 3	tons (short)	1 ton (short)	**907.184 74**	kg
1 t	1.102 311	tons (short)	1 ton (short)	**0.907 184 74**	t
1 kg	0.000 984 21	tons (long)	1 ton (long)	**1016.046 908 8**	kg
1 t	0.984 206 5	tons (long)	1 ton (long)	**1.016 046 908 8**	t
		CONCENTRATION			
1 g/t	0.029 166 6	ounce (troy)/ ton (short)	1 ounce (troy)/ ton (short)	34.285 714 2	g/t
1 g/t	0.583 333 33	pennyweights/ ton (short)	1 pennyweight/ ton (short)	1.714 285 7	g/t

OTHER USEFUL CONVERSION FACTORS

	Multiplied by	
1 ounce (troy) per ton (short)	20.0	pennyweights per ton (short)
1 pennyweight per ton (short)	0.05	ounces (troy) per ton (short)

Note: Conversion factors which are in bold type are exact. The conversion factors have been taken from or have been derived from factors given in the Metric Practice Guide for the Canadian Mining and Metallurgical Industries, published by the Mining Association of Canada in co-operation with the Coal Association of Canada.

MAPS
NOT
FILMED

CARTES
OMISES